



TECHNICAL DATA BULLETIN

INSTAbond® 122

Liquid Anaerobic Sealant

PRODUCT DESCRIPTION:

N INSTAbond® 122 is a low strength threadlocking compound designed for fastener diameters of ¼" (6 mm) and smaller. Has moderate chemical resistance and quick fixture time. Parts can be separated using hand tools. INSTAbond® 122 complies with MIL-S-46163 Type II Grade M / ASTM D 5363-03 AN0311.

Physical Properties (Uncured)

Parameters	Test Method	Specification
Color	-----	Purple
Viscosity, 25 deg C	ASTM D445	1,200 cPs
Specific Gravity, 25 deg C	ASTM D792	1.1 gms/ml
Flash Point	ASTM D56	>93 deg C
UV Light Properties	-----	Illumination @ 230 nm

CURED PROPERTIES

Properties	Specifications
Fixture Time:	
Unprimed steel @ 25 °C	5-10 minutes
*Primed steel @ 25 °C	3-5 minutes
Full Cure:	
Unprimed steel @ 25 °C	18 hours
*Primed steel @ 25 °C	12 hours
Breakaway Torque, 24 hours @ 25°C	8.5 N-m
Prevailing Torque, 24 hours @ 25°C	5.1 N-m
Hot Strength, 2 hours @ 93 deg C	5.8 (breakaway torque)
Solvent Resistance: (Breakaway Torques)	
Distilled Water	8.4 N-m
n-Butanol	6.5 N-m
Toluene	5.2 N-m
Motor Oil (10W-30)	7.8 N-m
JP-4 Jet Fuel	5.0N-m
Ethylene Glycol	5.8 N-m
Temperature Range	-65 – 300 deg F



8848 Hacks Cross Rd
Olive Branch, MS 38654
Fax (662) 895-4439
www.accrabond.com
Phone (662) 895-4480

GENERAL INFORMATION

This product is not recommended for use in pure oxygen and/or oxygen rich systems and should not be used with a sealant for chlorine-containing constituents or other strong oxidizing materials. This product is not suitable for use on plastic parts. Refer to Material Safety Data Sheet for instructions on safe handling of this material.

STORAGE

This product should be stored less than 100 deg F and out of direct sunlight. Product should be stored in the original, closed container. NEVER combine liquid primers/activators with anaerobic sealing compounds as violent chemical reactions will result. Shelf life is 18 months when stored in accordance with manufacturer's recommendations.

DIRECTIONS FOR USE

Substrates should be cleaned and degreased with a solvent such as acetone, MEK, or trichloroethylene. Do use mineral spirits or Stoddard solvent. Allow substrates to dry completely before applying sealing compound. Apply sealing compound to both surfaces and assemble. For faster cure speed and maximum bonding, apply INSTAbond® Primer N, INSTAbond® Primer T or INSTAbond® Primer F prior to application of sealing compound. Allow primer to dry thoroughly before applying sealing compound. Once fixturing has occurred, no adjustments should be made as this will decrease the sealing compound's total locking strength once the fixture bond is broken.

NOTE

The information contained in this document is furnished for information only and it's believed to be reliable based on previous evaluations. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for user's application based on user's production methods. This data should only be used as a guide for determining feasibility for a particular application.

PRODUCT INFORMATION CONTAINED HEREIN IS INTENDED FOR REFERENCE ONLY. MATERIAL SAFETY DATA INFORMATION AVAILABLE AT (662) 895-4480 OR IN WRITNG TO: ACCRAbond, Inc. 8848 Hacks Cross Road, Olive Branch, MS 38654, www.accrabond.com.