# SPECIFICATION DATA SHEET

TS-9016 Thermo-Tork<sup>®</sup>/Nonasbestos Gasket Material F729900E09M9

#### **Description:**

TS-9016 has a fully cured styrene butadiene rubber binder and a blend of Aramid and cellulose fibers. It is intended for oil and water applications with short duration maximum temperatures up to 290°C (550°F).

## **Specification Properties:**

| <u>Property</u>                 | <u>Value</u>                  | <u>Method</u> |
|---------------------------------|-------------------------------|---------------|
| Density, g/cc(lb/cu.ft)         | 1.44 (90) (min.)              | ASTM F 1315   |
| Compressibility, % (at 34.5MPa) | 10 - 25                       | ASTM F 36     |
| Recovery, %                     | 40 (min.)                     | ASTM F 36     |
| Tensile Strength, AMD, MPa(psi) | 12.41 (1800) (min.)           | ASTM F 152    |
| Fluid Resistance, IRM903 Oil    |                               | ASTM F 146    |
| Change in Thickness, %          | 25 - 65                       |               |
| Fluid Resistance, Fuel B        |                               | ASTM F 146    |
| Change in Thickness, %          | 10 - 40                       |               |
| Binder Type                     | Fully Cured Styrene Butadiene |               |

### **Remarks and Related Documents:**

Specification values determined by the test methods required for ASTM F-104, Type 7 materials.

EnCore®, Hydro-Fused®, MicroPore®, Pro-Formance®, Select-a-Seal®, Syntheseal®, Thermo-Tork®, and Voltoid® are registered trademarks of Interface Performance Materials, Inc. Select-a-Shield is a trademark of Interface Performance Materials, Inc.

WARNING: The description and performance data provided herein constitute a material specification for quality control purposes, but do not imply suitability for use in a specific application. Your specific application should not be undertaken without independent study and evaluation for suitability. Failure to select proper sealing products may result in either property damage or personal injury. For specific application recommendations, contact Interface Performance Materials. INTERFACE PERFORMANCE MATERIALS EXPRESSLY DISCLAIMS ALL WARRANTIES EITHER EXPRESS OR IMPLIED, INCLUDING ANY IMPLIED WARRANTY OF MERCHANTABILITY OR OF FITNESS FOR A PARTICULAR PURPOSE. IN NO EVENT WILL ISI BE LIABLE FOR ANY INDIRECT, SPECIAL, INCIDENTAL, CONSEQUENTIAL OR PUNITIVE DAMAGES, HOWEVER CAUSED AND ON ANY THEORY OF LIABILITY, WHETHER IN CONTRACT, STRICT LIABILITY, OR TORT (INCLUDING NEGLIGENCE OR OTHERWISE) ARISING IN ANY WAY OUT OF THE USE OF THE INFORMATION CONTAINED IN ITS SPECIFICATION DATA SHEETS, ITS PRODUCTS OR THEIR FUTURE USE BY YOU OR ANY THIRD PARTIES, EVEN IF ADVISED OF THE POSSIBILITY OF SUCH DAMAGE.

Specification Data Sheet Revised 07/01/15 ©2015 Interface Performance Materials, Inc

#### For more information, please visit www.InterfaceMaterials.com or contact

WORLD HEADQUARTERS Interface Performance Materials, Inc. 216 Wohlsen Way Lancaster, PA 17603 USA +1.717.207.6000

TECHNICAL CENTER Interface Performance Materials, Inc. 215 Wohlsen Way Lancaster, PA 17603 USA +1.717.207.6000

NORTH AMERICA Interface Performance Materials, Inc. 22260 Haggerty Road, Suite 200 Northville, MI 48167 USA +1.248.596.2800

ASIA PACIFIC Interface Sealing Solutions Shanghai Co., LTD Unit 14F, No. 728 Yan An Road West, Changning District Shanghai 200050 China +8621.5238.5650

EUROPE & SOUTH AMERICA Interface Sealing Solutions Europe Lili Pean, Le Bourg Bonloc 64240 France +33.5.5929.1220

#### GERMANY Interface Performance Materials Altenkirchen GmbH P.O. Box 12 63 Koblenzer Strasse Altenkirchen D-57610

Germany +49.2681.80020

