

## Medium Firm, Micro-Cellular Polyurethane Foam

Saint-Gobain NORSEAL® K40 series is a medium deflection urethane foam with minimal compression set and low out-gassing that exceeds fogging requirements. Ideal for controlling unwanted energy, these special formulations protect sensitive components by damping shock, dissipating motion, isolating vibration and absorbing impact energy.

NORSEAL K40 series is specially designed to provide the following features:

- Excellent compression set resistance
- Highly resilient (will not collapse)
- Dissipates stress
- Resistant to moisture and most chemicals
- Conformable and flexible even in extreme environmental conditions
- Easy to achieve intricate die-cut parts
- Aggressive acrylic adhesive (optional) facilitates assembly

### Available Sizes

Standard thickness: .063, .093, .125, .188 and .25 in. (1.6, 2.4, 3.2, 4.8 and 6.4 mm)

Master roll size: 54 in. (1371 mm) width. Length varies with thickness.

### Other Micro-Cellular Urethane Foams

Saint-Gobain has developed a full line of micro-cellular foams. By varying the modulus and density, we have created a broad product group that is categorized by degree of deflection force.



### Applications

- Electrical enclosures
- Automotive instrument panels
- Electronic gasketing
- Cellphones
- Appliance/office equipment
- Foot pads
- Vibration damping
- Cushioning
- Acoustical control
- Spacers

## NORSEAL® K40 Series – Properties

(Formerly known as Korel®)

Performance tests are run using standard test procedures. The values presented are typical values and should not be used for specification purposes.

Property	Test Method	K40
<b>Physical</b>		
Density: lb/ft <sup>3</sup> (kg/m <sup>3</sup> )	ASTM D3574	20 (320)
Thickness: inches (mm)	—	.063, .093, .125, .188, .250 (1.6, 2.4, 3.2, 4.8, 6.4)
Standard Color	—	Black
Compression Set: % @ 73°F (23°C) @158°F (70°C)	ASTM D3574 Test D	< 2 < 7
Compression Force Deflection: psi (kPa) 12.7 mm/min @ 25% Deflection	ASTM D3574 Test C	10 (69)
Force to Compress @ 25%, psi (kPa)	ASTM D1667	18 (124)
Hardness: Durometer	Shore O	53
Tear Strength: pli (kN/m)	ASTM D624 Die C	26 (4.6)
Tensile Elongation: %	ASTM D3574	380
Tensile Strength: psi (kPa)	ASTM D3574	198 (1363)
Modulus: psi (kPa)	ASTM D3574	85 (587)
<b>Thermal</b>		
Temperature Resistance Recommended Constant Use, max Recommended Intermittent Use, max	— —	158°F (70°C) 250°F (121°C)
Thermal Conductivity: BTU-in/hr-sq ft°F (W/m-C)	ASTM E1530	0.6 (0.086)
<b>Environmental</b>		
Fogging	SAE-J 1756, 3 hrs. @ 212°F (100°C)	Pass
Outgassing: TML % CVCM % WVR %	ASTM E595, 24 hr. @ 257	1.18 0.25 —
Water Absorption: % wt. gain	AMS 3568-95	10
<b>Electrical</b>		
Surface Resistivity: ohm/sq	ASTM D257	1.5 x 10 <sup>13</sup>
Volume Resistivity: ohm.cm	ASTM D257	3.2 x 10 <sup>14</sup>
Dielectric Strength: volts/mil	ASTM D149	47

## NORSEAL® K40 – Standard Roll Sizes

Product No.	Thickness in. (mm)	Length ft. (m)
K40-063	.063 (1.5)	200 (61)
K40-093	.093 (2.4)	100 (30.5)
K40-125	.125 (3.2)	100 (30.5)
K40-188	.188 (4.8)	50 (15.3)
K40-250	.25 (6.4)	50 (15.3)

### Options (subject to minimum order requirements)

Acrylic pressure-sensitive adhesive (PSA) available on one side.

### Important Instructions

- Because Saint-Gobain cannot anticipate or control every potential application, we strongly recommend testing of this product under individual application conditions prior to commercial use.
- Recommended service temperature is between -40° to 158°F (-40° to 70°C).
- For PSA option, surfaces must be clean and free of oil, grease, moisture, dust and dirt. Isopropyl alcohol is good for cleaning the surface. Do not remove liner until tape is in proper position. Avoid touching adhesive surface before application.

### Shelf Life

12 months after the date of sale when stored in original packaging at temperatures up to 70°F (21°C) and 50% relative humidity.

NORSEAL® is a registered trademark of Saint-Gobain Performance Plastics.



#### Saint-Gobain Performance Plastics

One Sealants Park  
Granville, NY 12832  
1-800-724-0883  
Tel: (518) 642-2200  
Fax: (518) 642-2793

[foams@saint-gobain.com](mailto:foams@saint-gobain.com)  
[www.foams.saint-gobain.com](http://www.foams.saint-gobain.com)

The data and details in this document were correct and up-to-date at the time of printing and are intended to provide information on our products and their possible applications. It is the user's responsibility to obtain the latest version of the product data sheet. This data sheet is not a specification and does not assure specific product characteristics or make reference to the suitability of the product for a specific application. Because Saint-Gobain cannot anticipate or control every application, we strongly recommend testing of this product under individual application conditions. The application, use and conversion of this product are the user's responsibility.

Limited Warranty: For a period of 6 months from the date of first sale, Saint-Gobain Performance Plastics warrants this product(s) to be free from defects in manufacturing. Our only obligation will be to provide replacement product for any portion proving defective, or at our option, to refund the purchase price thereof. User assumes all other risks, if any, including the risk of injury, loss or damage, whether direct or consequential, arising out of the use, misuse, or inability to use this product(s).

SAINT-GOBAIN PERFORMANCE PLASTICS DISCLAIMS ANY AND ALL OTHER WARRANTIES, EXPRESSED OR IMPLIED, INCLUDING THE IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE.

NOTE: Saint-Gobain Performance Plastics Corporation does not assume any responsibility or liability for any advice furnished by it, or for the performance or results of any installation or use of the product(s) or of any final product into which the product(s) may be incorporated by the purchaser and/or user. The purchaser and/or user should perform its own tests to determine the suitability and fitness of the product(s) for the particular purpose desired in any given situation.