

AUTOMOTIVE



Ensolite® IV2

- UL 94 HF-1 and HBF listed for flame
- UL 50E (periodic and continuous compression) listed for gaskets and seals (recent upgrade)
- ASTM D 1056-07 2A2 / 2C2 / 2B2 grade product
- ASTM D 6576-07 Type II, Grades A & B, Condition Soft-Medium material
- PVC / NBR / CR closed cell rubber material manufactured in continuous rolls

Ensolite®

General Information

Armacell Ensolite® IV2: Armacell LLC (Conover, NC Plant) manufactures a black, continuous, closed cell, medium density (5.5 - 7.5 lb./ft³) (88 - 120 kg/m³) PVC/NBR/CR rubber product IV2, that meets all the physical property requirements of ASTM D 1056-07 2A2 / 2C2 / 2B2 and SAE J-18 APR2002 2A2 / 2C2 / 2B2. IV2 has excellent resistance to oil and fuel. IV2 meets the requirements of FMVSS-302 at most thicknesses and is listed to UL 94 HF-1 at 1.1 mm (0.043”) and higher and UL 94V-0 at 11.7 mm (0.461”) and higher (UL File# QMFZ2.E55798). IV2 meets the flame resistance requirements of CAL 117 (tested at 0.500”) and FAR 25.853 a(2003) 12 second vertical burn at 1/8” & 1/4”. IV2 is listed with UL to UL 50E (periodic and continuous compression) (UL File# JMST2.MH10189). IV2 is listed on the approved source list of Chrysler MSAY 516 Type 2. Standard roll widths: 54” or 60”.

Automotive and Industrial Specifications

The following is a list of automotive and industrial specifications that Armacell Ensolite® IV2 has been tested to or can meet. Additional specifications are listed that have a few exceptions. Feel free to suggest other automotive, military or industrial specifications, and a full review will be made.

Source	Specification	IV2	Comments
ASTM	ASTM D1056-07	2A2 / 2C2 / 2B2	Additional (optional) suffixes can be added
ASTM	ASTM D 6576-07	Type II, Grades A & B, Condition Soft-Medium	Formerly MILR6130-C
CAL	CAL 117	Pass	Flame resistance
Caterpillar	1E0720	1E0720E (Medium) Grades 2 and 3	No exceptions
Chrysler	Chrysler MSZ-75 J18	2A2 / 2C2 / 2B2	Additional (optional) suffixes can be added
Chrysler	Chrysler MS JP9-4	Meets at most thicknesses	Flame resistance (horizontal burn rate)
Chrysler	Chrysler MSAY 516	Type 2	Approved source list

Automotive and Industrial Specifications (continued)

Source	Specification	IV2	Comments
Federal	FMVSS-302	Meets at most thicknesses	Flame resistance (horizontal burn rate). See note 1
Federal	FAR 25.853	Pass at 1/8" and 1/4"	12 Second Vertical Burn Test. (Test report available upon request)
FORD	FORD WSK M2D 419-A	Type 3	See note 2
GM	GM 6086-M	Type II	CD tested at 50% deflection. See note 3
GM	GM 6090-M	(B4A) Meets at thicknesses of 2.5mm (.098") and higher	Flame resistance tested per GM 9070-P (horizontal burn rate)
GM	GMN11106	Type II	CD tested at 50% deflection. See note 3
GM	GMW15473	Class I Type IV	CD tested at 50% deflection. See note 3
ISO	ISO 6916	2A1 / 2C1 / 2B1. Pass, no migration staining	Exception to compression set. Tested to Suffix P
Military	ASTM D 6576-07	Type II, Grades A & B, Condition Soft-Medium	Formerly MILR6130-C
SAE	SAE J18 APR2002	2A2 / 2C2 / 2B2	Additional (optional) suffixes can be added
SAE	SAE J369	Meets at most thicknesses	Flame resistance (horizontal burn rate)
SAE	SAE J 1351	Pass, rating 2	Odor specification
Toyota	TSM 1501G	2A1 / 2C1 / 2B1. Pass, no migration staining	Exception to compression set. Tested to Suffix P
Toyota	TSM 0500G	Meets at most thicknesses	Flame resistance (horizontal burn rate)
UL	UL94 HF-1	HF-1 UL Listed at 1.1 mm (.043") and higher	Flame resistance specification. (UL file# QMFZ2.E55798)
UL	UL94 HBF	HBF UL Listed at 1.1 mm (.043")	Flame resistance specification. (UL file# QMFZ2.E55798)
UL	UL 50E	Suitable as gasket material for UL 50 and UL 50E (continuous and periodic compression) enclosures	Request additional information about UL enclosure types. (UL file# JMST2.MH10189)

Note 1: A number of horizontal burn tests can also be listed (GM 6090, BMW, Volvo, etc.). Request additional information.

Note 2: For all FORD WSK M2D 419-A callouts, request full information for each product due to some exceptions with non-tested staining requirements.

Note 3: For all GM 6086-M, GMN11106 & GMW15473 callouts, Armacell (Ensolite®) certifies to the "basic" requirements only. Request additional information for each product. Providing application (interior, exterior or under-hood) and part thickness is helpful.

Roll Size Information

Gauge (in)	Gauge (fraction of an inch)	Gauge (mm)	Tolerance (inches)	Tolerance (mm)	Roll Size W (in)	Roll Size L (ft)	Roll Size W (m)	Roll Size L (m)	Comments
1.25	1-1/4	31.75	1.25 - 1.45	31.75 - 36.83	54	50	1.37	15.24	S2S, NS
1.25	1-1/4	31.75	1.25 - 1.45	31.75 - 36.83	54	50	1.37	15.24	S2S, L
1.25	1-1/4	31.75	1.25 - 1.45	31.75 - 36.83	60	50	1.52	15.24	S2S
1.25	1-1/4	31.75	1.25 - 1.45	31.75 - 36.83	62	100	1.57	30.48	S2S
1.50	1-1/2	38.10	1.50 - 1.70	38.10 - 43.18	54	100	1.37	30.48	S2S
1.57		40.00	1.57 - 1.77	39.90 - 45.00	40	50	1.02	15.24	S2S

S2S = skin 2 sides

L = additional lengths available

NS = no splice



IV2 Continuous Rolls/Sheets (Black)

Physical Properties	Unit	Test Method	Typical Results
Density	kg/m ³	ASTM D 1056	88 - 120
	lb/ft ³	ASTM D 1056	5.5 - 7.5
Hardness, Durometer Shore 00		ASTM D 2240	55 ± 10
Compression Deflection (25%)	kPa	ASTM D 1056	80 - 144
	psi	ASTM D 1056	5.0 - 9.0
50% Compression Set (Room temp)	%	ASTM D 1056	≤ 35%
Tensile Strength	kPa	ASTM D 412 (Die A)	517 minimum
	psi	ASTM D 412 (Die A)	75 minimum
Tear Strength	kN/m	ASTM D 624 (Die C)	2.1
	lb/in	ASTM D 624 (Die C)	12
Elongation	%	ASTM D 412 (Die A)	100 minimum
Service Temperature (1)			
Low	°F (°C)	ASTM D 746	-40°F (-40°C)
High Continuous	°F (°C)	ASTM D 746	---
High Intermittent (2)	°F (°C)	ASTM D 746	200 °F (93.3°C)
Water Absorption			
Maximum Weight Change	%	ASTM D 1056	< 10%
Fluid Immersion (7 days at 23°C [73.4°F])			
ASTM Ref. Fuel B, Weight Change (%)	%	ASTM D 1056	< 100%
Accelerated Aging (7 days at 70°C [158°F])			
Flexibility (180° bend without cracking)		ASTM D 1056	Pass
Appearance change		ASTM D 1056	None
Change in Compression Deflection	%	ASTM D 1056	± 30%
Combustion Characteristics (3)		Thicknesses	Comments
FMVSS-302			Pass at most thicknesses
FAR 25.853		1/8" (3.18 mm) & 1/4" (6.35 mm)	Pass
UL94			
HF-1		0.043" (1.1 mm) & higher	Listed, UL file# QMFZ2.E55798
HBF		0.043" (1.1 mm) & higher	Listed, UL file# QMFZ2.E55798

ASTM D 1056 designation: 2A2 / 2C2 / 2B2
 SAE J 18 APR2002 designation: 2A2 / 2C2 / 2B2
 ASTM D 6576: Type II, Grades A & B, Condition Soft-Medium
 Additionally UL Listed to UL 50E (UL file# JMST2.MH10189)
 IV2 is on the approved source list for Chrysler MSAY 516 (Type 2)
 Standard Roll Width: 54" (1.37 m)
 Maximum Gauge: 1.50" (38.10 mm)

(1) This recommendation is based on polymer type only. For specific application requirements please contact technical service.

(2) This temperature is the maximum allowable for intermittent exposure only. For continuous use temperature please contact technical service.

(3) Flammability – This item and any corresponding data refer to typical performance in the specific test indicated and should not be construed to imply this material's behavior in other fire conditions.

NBR – Acrylonitrile Butadiene Rubber

PVC – Polyvinyl Chloride

CR – Chloroprene (Neoprene)

UL File Number for Armacell Ensolite® IV2

UL File Number: QMFZ2.E55798
Plastics – Component [UL94]

									H	D	
		Min.		H	H	R T I			V	4	C
		Thk	Flame	W	A	Elec	Mech		T	9	T
Material Dsg	Color	mm	Class	I	I		Imp	Str	R	5	I

Nitrile Rubber/Polyvinylchloride/Neoprene(NBR/PVC/CR), closed-cell foam, “Ensolite”, furnished as profiles, tubes or sheets.

IV2 (o)	BK	1.1	HF-1	-	-	50	-	50	-	-	-
		12.4	HF-1	-	-	50	-	50			

(o) - Density range 0.092 - 0.105 g/cc w/o skin and 0.107 - 0.204 g/cc w/ skin

File Number: JMST2.MH10189

UL Spec	UL Spec	UL Spec
IV1, IV2, IVC	Closed cellular PVC/NBR/CR gasket material	Types “IV1”, “IV2”, “IVC”. Suitable as a gasket material for UL 50 enclosure types 2, 3, 3R, 3S, 4, 4X, 5, 6, 6P, 12, 12K and 13. [UL50E (Continuous and Periodic Compression)]
UL Spec	Test Method	Requirements
UL 50E	Tensile strength and elongation after heat aging 168 h (7 d) at 158°F (70°C)	75% of original for tensile strength 60% of original for elongation
UL 50E	Oil immersion / oil aging (IRM # 903), % volume change after 70 h @ room temperature	Shall not swell more than 25% or shrink more than 1% of original volume
UL 157	Tensile strength and elongation after heat aging 70 h @ 212°F (100°C)	60% of original (For both tensile and elongation)

UL Yellow Card Listing Verification Online

To obtain verification online:

1. www.ul.com
2. Click on "Certifications"
3. Click on "Company Name" in the general search area
4. Type in "Armacell" & click "Search"
5. 8 (Eight) Armacell file numbers come up (2 belong to Armacell Germany)
 - For Armacell *Ensolute*[®] & *Monarch*[®] products (Flame / UL94)
Click on QMFZ2.E55798
 - For Armacell *Ensolute*[®] products listed to JMST2 (Gaskets & Seals)
Click on JMST2.MH30018 and JMST2.MH10189
 - For Armacell *Monarch*[®] products listed to JMLU2 (Gaskets & Seals)
Click on JMLU2.MH25062

Vertical Flame / 12 Second Burn per FAR 25.853 Appendix F — Part I Test Criteria and Procedures for Showing Compliance with Sec. 25.853 or Sec. 25.855

Armacell Ensolute [®] Product #	Min. Thickness	Pass / Fail	Independent Test Lab Report	Test Report ID #	Polymer	ASTM D 1056 Grade	Density lb./ft ³	25% CD (psi)
IV2	1/4"	Pass	2/18/10	0148	PVC/NBR/CR	2B2	5.5 - 7.5	5 - 9
IV2	1/8"	Pass	2/18/10	0147	PVC/NBR/CR	2B2	5.5 - 7.5	5 - 9

ARMACELL LLC
 TEL: 1 800 866-5638
 FAX: 919 304-3847
 info.us@armacell.com
 www.armacell.us

7600 Oakwood Street Extension • Mebane, NC 27302



Armacell provides this information as a technical service. To the extent the information is derived from sources other than Armacell, Armacell is substantially, if not wholly, relying upon the other source(s) to provide accurate information. Information provided as a result of Armacell's own technical analysis and testing is accurate to the extent of our knowledge and ability, as of date of printing, using effective standardized methods and procedures. Each user of these products, or information, should perform their own tests to determine the safety, fitness and suitability of the products, or combination of products, for any foreseeable purposes, applications and uses by the user and by any third party to which the user may convey the products. Since Armacell cannot control the end use of this product, Armacell does not guarantee that the user will obtain the same results as published in this document. The data and information are provided as a technical service and are subject to change without notice.