



CCTC
三环集团

潮州三环（集团）股份有限公司
Chaozhou Three-Circle (Group) Co., Ltd.
地址：廣東省潮州市鳳塘三環工業城 郵編(Post Code)：515646
ADD : San Huan Industrial District, Feng Tang Chao Zhou, GuangDong, China

承 认 书

SPECIFICATION FOR APPROVAL

客户名称:

CUSTOMER:

产品名称 多层片式瓷介电容器

PARTNAME: Multilayer Chip Ceramic Capacitor

产品规格 LED 用 MLCC 系列

SPECIFICATION: MLCC FOR LED SERIES

承认书编号

APPROVAL SHEET NO.: DRAAW108E/1-2015

发出日期

ISSUED DATE:

制造 MANUFACTURER			客户 CUSTOMER		
批准 APPROVED	审核 CHECKED	经办 PREPARED	批准 APPROVED	审核 CHECKED	经办 PREPARED
王艳红	王炳林	张国信			

潮州三环（集团）股份有限公司

地址：中国广东省潮州市凤塘三环工业城

电话：86-768-6855932

传真：86-768-6855921

网址：HTTP://WWW.CCTC.CC



潮州三环（集团）股份有限公司

Chaozhou Three-Circle (Group) Co., Ltd.

地址：廣東省潮州市鳳塘三環工業城 郵編(Post Code) : 515646

ADD : San Huan Industrial District, Feng Tang Chao Zhou, GuangDong, China

文件编号	DRAAW108E/1-2015			页数	25
文件名称	多层片式陶瓷电容器(产品承认书)			制订日期	2015.06
版数	制定、修订日期	页数	制定、修订内容		登记者
E/0	2014-8-19	24	新制定		王彬彬
E/1	2015-6-25	25	调整注意事项		王彬彬



产品标准书	编 号 Document No.
SPECIFICATION FOR APPROVAL	DRAAW108E/1-2015

目录

1、 电容器及介质分类-----	第 03 页
2、 应用场合-----	第 04 页
3、 选型注意-----	第 04 页
4、 使用注意事项-----	第 05 页
5、 产品命名-----	第 12 页
6、 阻容降压产品容量范围-----	第 13 页
7、 产品尺寸-----	第 14 页
8、 技术要求和测试条件-----	第 14 页
9、 产品包装-----	第 20 页
10、 产品环保状况-----	第 24 页



潮州三环（集团）股份有限公司

Chaozhou Three-Circle (Group) Co., Ltd.

地址：廣東省潮州市鳳塘三環工業城 郵編(Post Code) : 515644

ADD : San Huan Industrial District, Feng Tang Chao Zhou, GuangDong, China

产品标准书 SPECIFICATION FOR APPROVAL	编 号 Document No. DRAAW108E/1-2015
--	--------------------------------------

1. 电容器及介质分类 Types of Capacitor and Dielectric Material

※X7T: 此类介质材料的电容器为II类电容器，具有较高的介电常数，容量比I类电容器高，具有较稳定的温度特性，相对常规的X7R产品，具有低损耗、高绝缘的特性，适用于电压较高的LED阻容降压场合。



※ X7T: material is a kind of material has high dielectric constant. The capacitor made of this kind material is considered as Class II capacitor whose capacitance is higher than that of class I. These capacitors are classified as having a semi-stable temperature characteristic and used over a wide temperature range, Compared with X7R material, it has lower DF and higher IR. It is suitable for LED circuit.

※X7R: 此类介质材料的电容器为II类电容器，具有较高的介电常数，容量比I类电容器高，具有较稳定的温度特性，适用于容量范围广，稳定性要求不高的电路中，如隔直、耦合、旁路、鉴频等电路中，可用于电压相对较低的LED阻容降压场合。

※ X7R: The capacitor made of this kind material is considered as Class II capacitor whose capacitance is higher than that of class I. These capacitors are classified as having a semi-stable temperature characteristic and used over a wide temperature range, such in these kinds of circuits, DC-blocking, decoupling, bypassing, frequency discriminating etc. It can also used in LED circuit with low voltage condition.

产品标准书	编 号 Document No.
SPECIFICATION FOR APPROVAL	DRAAW108E/1-2015

2. 应用场合 Applications



3. 选型注意 Applications

为了确保产品的使用寿命，需留足余量，请参照以下建议选型：

MLCC 产品额定电压是指最大正常工作的直流电压，在阻容降压中，选择的电容工作电压不低于产品两端实际交流电压的 2 倍；

如使用在 220V_{ac} 场合，建议选用 450V 电压产品，如使用在 120V_{AC} 场合，建议选择 250V 电压产品。

To insure the life of the products, add components margin is recommended . Please refer to the advice below:

The rated voltage means the product can be used in the condition with the maximum DC voltage for long time . In this LED condition , The select voltage must be twice of the AC voltage .

If the voltage is 220 V_{ac}, select 450V rated voltage is recommended . If the voltage is 120 V_{ac}, select 250V rated voltage is recommended .

产品标准书 SPECIFICATION FOR APPROVAL	编 号 Document No. DRAAW108E/1-2015
---	--

4. MLCC 使用注意事项 Precautions on the use of MLCC

4.1 电路板设计 PCB Design

4.1.1 电路板图案设计 Design of Land-patterns

下面图和表格给出了部分推荐的设计图案，可以防止安装时焊锡量过多。

同时也给出了不正确的图案。

The following diagrams and tables show some examples recommended patterns to prevent excessive solder amounts (larger fillets which above the component end terminations)

Examples of improper pattern designs are also shown.



电路板设计推荐图案尺寸：

Recommended land dimensions for a typical chip capacitor land patterns for PCBs

波峰焊接时推荐设计的尺寸 (单位: mm):

Recommended land dimensions for wave-soldering (unit: mm)

规格 SIZE		1210
尺寸	L	3.2
	W	1.6
A		1.8~2.5
B		0.8~1.7
C		1.8~2.5



再流焊接时推荐设计的尺寸 (单位: mm)

Recommended land dimensions for reflow-soldering (unit: mm)

规格 SIZE		1210	1812	2220	2225
尺寸	L	3.2	4.5	5.7	5.7
	W	2.5	3.2	5.0	6.4
A		1.8~2.5	2.5~3.4	4.0~4.6	4.0~4.6
B		1.0~1.5	1.8~2.0	2.0~2.2	2.0~2.2
C		1.6~3.2	2.3~3.5	3.5~4.8	5.0~6.2







过量的焊锡会影响产品抵抗机械应力的能力，因此在设计图案时应引起注意。

Excess solder can affect the ability of chips to withstand mechanical stresses. Therefore, please take proper precautions when designing land-patterns.

在应用中一些焊接好与坏的情况：

Examples of good and bad solder application

产品标准书 SPECIFICATION FOR APPROVAL	编 号 Document No. DRAAW108E/1-2015
--	---



项目 Item	不推荐结构 Not recommended	推荐结构 Recommended
片状元件和带引线的元件的混合焊接 Mixed mounting of SMD and leaded component	 <p>lead wire of component soldering iron</p>	 <p>solder resist</p>
靠近底座的焊接 Component placement close to the chassis	 <p>chassis solder (for grounding)</p>	 <p>solder-resist</p>
在片状元件附近带引线元件的焊接 Hand-soldering of leaded components near mounted components	 <p>lead wire of component soldering iron</p>	 <p>solder resist</p>

4.1.2 图案结构

Pattern configurations


下面是电容器安装好与坏的例子。选择贴装位置，应尽可能减小电路板在弯曲时受到的机械应力。

The following are examples of good and bad capacitor layout, SMD capacitors should be located to minimize any possible mechanical stresses from board warp or deflection..

	不推荐结构 Not recommended	推荐结构 Recommended
电路板弯曲 Deflection of the board		

对于电路板分拨的电容器，在分拨时受到的机械应力大小与电容器的安装有关。下面推荐了一些好的设计。

To layout the capacitors for the breakaway PC board, it should be noted that the amount of mechanical stresses given depending on capacitor layout. The example below shows recommendations for better design.

产品标准书
编 号 Document No.
SPECIFICATION FOR APPROVAL
DRAAW108E/1-2015






在沿着分拨线分拨电路板时，对产品施加的机械应力与使用的方法关系很大。分折电路板时片状元件受到的疲劳按照如下顺序增大：分折、剪切、V型槽、穿孔。因此，贴装时应该考虑电路板的分拨过程。




When breaking PC boards along their perforations, the amount of mechanical stress on the capacitors can vary according to the method used. The following methods are listed in order from least stressful to most stressful: push-back, silt, -grooving, and perforation. Thus, any ideal SMD capacitor layout must also consider the PCB splitting procedure.

4.2 自动贴装注意事项 Considerations for automatic placement

贴装机的调整 Adjustment of mounting machine

- ①. 产品在电路板贴装时，不应该受到过大的冲击。
 - ②. 必须定期对吸头和定位爪进行检查、维修和更换
- ①. Excessive impact load should not be imposed on the capacitors when mounting the PC boards.
- ②. The maintenance and inspection of the mounters should be conducted periodically.


	不推荐结构 Not recommended	推荐结构 Recommended
单面贴装 Single-sided mounting		
双面贴装 Double-sided mounting		

产品标准书 SPECIFICATION FOR APPROVAL	编 号 Document No. DRAAW108E/1-2015
4.3 推荐焊接曲线 Recommended soldering profile	
4.3.1 说明: ① 产品推荐使用回流焊接工艺; ② 大尺寸产品适用于回流焊接工艺	
4.3.1 Re: ①flow Soldering is recommended; ②flow soldering is suitable for bigger size MLCCs	
4.3.2 锡铅焊接曲线 Recommended Sn&Pb soldering profile 再流焊 Reflow soldering	
	
注意 Caution	
①. 理想状况的焊锡高度为电容器厚度的 $1/2 \sim 1/3$, 如下图所示: ①.The ideal condition is to have solder mass (fillet) controlled to $1/2$ to $1/3$ of the thickness of the capacitor, as shown below:	
	
②. 过长的焊接时间会影响端头的可焊性, 焊接时间尽可能保持与推荐时间一致。 ②. Because excessive dwell times can detrimentally affect solderability, soldering duration should be kept as close to recommended times as possible.	
波峰焊 Wave solder profile	
	


产 品 标 准 书	编 号 Document No.
SPECIFICATION FOR APPROVAL	DRAAW108E/1-2015

注意 Caution

- ①. 确保电容器充分预热。
- ②. 产品预热和焊接温度差不超过 100~130°C。
- ③. 焊接后尽可能慢速冷却。
- ①. Make sure the capacitors are preheated sufficiently.
- ②. The temperature difference between the capacitor and melted solder should not be greater than 100 to 130°C.
- ③. Cooling after soldering should be gradual as possible.


手工焊接 Hand soldering

注意 Caution

- ①. 用尖端最大直径 1.0mm 功率 20W 的焊接烙铁。
- ②. 焊接烙铁不要直接接触产品。
- ①. Use a 20w soldering iron with a maximum tip diameter of 1.0mm.
- ②. The soldering iron should not directly touch the capacitor.

4.3.3 无铅焊接曲线 Recommended Pb-Free soldering profile
回流焊接 Reflow soldering


产品 标 准 书 SPECIFICATION FOR APPROVAL	编 号 Document No. DRAAW108E/1-2015
--	--

波峰焊接 Wave solder profile



4.4 分拨电路板 Handling

Breakaway PC boards (splitting along perforations)

- (1). 在电容器或其它贴装后，必须注意因电路板弯曲或变形带来的应力。
- (2). 分拨电路板时必须使用专用的夹具，不可以用手拔断。
- (1). When splitting the PC board after mounting capacitors and other components, care is required so as not to give any stresses of deflection or twisting to the board.
- (2). Board separation should not be done manually, but by using the appropriate devices.

4.5 保存 Storage

- (1). 在下列环境中保存产品：温度 5~40°C；湿度 ≤70% RH
- (2). 产品自生产之日起保存期为一年，产品使用之前请勿拆开编带。
- (3). 编带拆开后，产品应在三个月内使用。
- (4). 高介电常数电容器 (X7R,X5R,Y5V) 的容值随时间会逐渐减小，所以在电路设计时应充分考虑这一现象。容值减小的电容器在 150°C 热处理 1 小时后容值会恢复到初试值。
- (1). Keep the storage environment conditions as following:
Temperature: 5~40°C
Humidity: ≤70% RH
- (2). Don't open the tape until the parts are to be used, and store them within one year since the date printed on the reel.
- (3). Use the chips within 3 months after the tape is opened.
- (4). The capacitance value of high dielectric constant capacitors (X7R,X5R,Y5V) will gradually decrease with the passage of time, so this should be taken into consideration in the circuit design. If such a capacitance reduction occurs, a heat treatment of 150°C for 1 hour will return the capacitance to its initial level.



潮州三环（集团）股份有限公司

Chaozhou Three-Circle (Group) Co., Ltd.

地址：廣東省潮州市鳳塘三環工業城 郵編(Post Code)：515644

ADD : San Huan Industrial District, Feng Tang Chao Zhou, GuangDong, China

产品标准书 SPECIFICATION FOR APPROVAL	编号 Document No. DRAAW108E/1-2015
--	-------------------------------------

4.6 MLCC 产品的电压及温度使用注意事项

4.6.1 工作温度方面

有必要选择高于使用温度以上的额定温度产品。另外，还需考虑机器内的温度分布以及季节性的温度变化。

当超过额定工作温度时会产生问题如在高于上限工作温度的条件下使用电容器，电容器会产生绝缘电阻低下、电流突然急剧增大或短路的问题。

电容器中使用了介电常数随温度变化的陶瓷介质,所以在使用温度范围较宽下，其静电容量可能会发生很大的变化。所以为了确保静电容量，我们推荐以下的方法：

(1) 在实际使用中控制使用温度范围，以此来抑制由于温度带来的静电容量变化率。

(2) 所谓的温度特性，即使周围温度在额定温度以下，随着温度的变化静电容量也可能产生变化。因此在时间恒定的回路等实效静电容量范围较小的回路上使用时，除了以上的内容，也请在考虑直流电压特性以及静电容量的放置特性之后选择电容器

4.6.1 额定电压方面

(1) 对电容器施加的电压,请控制在规格书中规定的额定电压以下。(推荐使用在额定电压的 70%以下使用)

如果是直流电压和交流电压组合起来使用的情况，请保持峰值电压之和 (Zero-to-peak 电压)在额定电压以下。用于交流或脉冲电压时，峰值电压之和 (Peak-to-peak 电压) 应低于额定电压。

如果在超过目录或规格书所规定的额定电压下使用电容器可能产生由于陶瓷介质的绝缘破坏导致的电气短路。另外，根据施加电压以及周围温度的不同，发生不良的时间也不同。

(2) 即使在额定电压以下使用，但如果在高速脉冲电压或高频交流电压下使用，也有可能导致电容器可靠性下降。

4.7 产品在较高的温度下使用，寿命会大幅降低，请客户在使用前做好相关的寿命试验。



潮州三环（集团）股份有限公司
Chaozhou Three-Circle (Group) Co., Ltd.
地址：廣東省潮州市鳳塘三環工業城 郵編(Post Code): 515644
ADD: San Huan Industrial District, Feng Tang Chao Zhou, GuangDong, China

产品标准书 SPECIFICATIONFOR APPROVAL	编 号 Document No. DRAAW108E/1-2015
<p>5. 产品命名</p> <p>Product Parts Numbering System</p> <p>(例) (example)</p> <p><u>TCC</u> <u>1812</u> <u>X7T</u> <u>224</u> <u>K</u> <u>451</u> <u>G</u> <u>T</u></p>	

产品标准书 SPECIFICATIONFOR APPROVAL	编 号 Document No.
	DRAAW108E/1-2015

6. 阻容降压产品容量范围

Product Capacitance Range


X7R

7R								
		1210		1812			2220/2225	
Cp	V _{DC}	100	250	100	200	450	100	250
104	F	F	G	G	G	G	G	G
154	H	H	H	H		G	G	G
224	G	G	H	H		G		G
334	G		G	G		G	G	G
364	G		G	G		G	G	
394	G		G	G		G	G	
474	G		G	G		G	G	
564	G		G			G	G	
84			G			G	G	
824	H		G			G	G	
15	H		G			G	G	

X7T

X7T									
		1210		1812		2220		2225	
Cp	V _{DC}	250	250	450	250	450	250	450	
104	G	G	G	G	G	G	G	G	
154	G	G	G	G	G	G	G	G	
22	G	G	G	G	G	G	G	G	
334	G	G	G	G	G	G	G	G	
364	G	G	G	G	G	G	G	G	
394	G	G	G	G	G	G	G	G	
474	G	G	G	G	G	G	G	G	
56				G	G	G	G	G	
684		G		G	G	G	G	G	
824		G		G	G	G	G	G	
105		G		G	G	G	G	G	

以上容量仅供参考，具体容量取决于使用要求

产品标准书 SPECIFICATION FOR APPROVAL	编 号 Document No. DRAAW108E/1-2015																																										
7. 产品尺寸 Dimensions																																											
规格: 1210、1812、2220、2225 Chip Size: 1210、1812、2220、2225																																											
																																											
<table border="1" style="width: 100%; border-collapse: collapse;"> <thead> <tr style="background-color: #ffffcc;"> <th style="text-align: left;">规格 Type</th><th style="text-align: center;">L (mm)</th><th style="text-align: center;">W mm</th><th style="text-align: center;">e (mm)</th><th style="text-align: center;">g min (mm)</th><th style="text-align: center;">T (mm)</th><th></th></tr> </thead> <tbody> <tr> <td>1210</td><td style="text-align: center;">3.20 ± 0.30</td><td style="text-align: center;">2.5 ± 0.20</td><td style="text-align: center;">0.3~0.8</td><td style="text-align: center;">1.6</td><td style="text-align: center;">1.60 ± 0.20</td><td style="text-align: center;">2.00 ± 0.2</td></tr> <tr> <td>1812</td><td style="text-align: center;">4.50 ± 0.30</td><td style="text-align: center;">3.2 ± 0.30</td><td style="text-align: center;">0.3~1.5</td><td style="text-align: center;">2.5</td><td style="text-align: center;">1.60 ± 0.20</td><td style="text-align: center;">2.00 ± 0.20</td></tr> <tr> <td>2220</td><td style="text-align: center;">5.70 ± 0.40</td><td style="text-align: center;">5.0 ± 0.40</td><td style="text-align: center;">0.3~1.1</td><td style="text-align: center;">3.5</td><td style="text-align: center;">—</td><td style="text-align: center;">2.00 ± 0.20</td></tr> <tr> <td>2225</td><td style="text-align: center;">5.70 ± 0.40</td><td style="text-align: center;">6.2 ± 0.40</td><td style="text-align: center;">0.3~1.1</td><td style="text-align: center;">3.5</td><td style="text-align: center;">—</td><td style="text-align: center;">2.00 ± 0.20</td></tr> <tr> <td></td><td></td><td></td><td></td><td></td><td></td><td style="text-align: center;">2.50 ± 0.30</td></tr> </tbody> </table>		规格 Type	L (mm)	W mm	e (mm)	g min (mm)	T (mm)		1210	3.20 ± 0.30	2.5 ± 0.20	0.3~0.8	1.6	1.60 ± 0.20	2.00 ± 0.2	1812	4.50 ± 0.30	3.2 ± 0.30	0.3~1.5	2.5	1.60 ± 0.20	2.00 ± 0.20	2220	5.70 ± 0.40	5.0 ± 0.40	0.3~1.1	3.5	—	2.00 ± 0.20	2225	5.70 ± 0.40	6.2 ± 0.40	0.3~1.1	3.5	—	2.00 ± 0.20							2.50 ± 0.30
规格 Type	L (mm)	W mm	e (mm)	g min (mm)	T (mm)																																						
1210	3.20 ± 0.30	2.5 ± 0.20	0.3~0.8	1.6	1.60 ± 0.20	2.00 ± 0.2																																					
1812	4.50 ± 0.30	3.2 ± 0.30	0.3~1.5	2.5	1.60 ± 0.20	2.00 ± 0.20																																					
2220	5.70 ± 0.40	5.0 ± 0.40	0.3~1.1	3.5	—	2.00 ± 0.20																																					
2225	5.70 ± 0.40	6.2 ± 0.40	0.3~1.1	3.5	—	2.00 ± 0.20																																					
						2.50 ± 0.30																																					
8. 技术要求和测试条件 Specification and Test Condition																																											
8.1 外观 Appearance																																											
<table border="1" style="width: 100%; border-collapse: collapse;"> <thead> <tr> <th style="text-align: left;">类型 Dielectrics</th><th style="text-align: center;">技术要求 Specification</th><th style="text-align: center;">测试条件 Testing Condition</th></tr> </thead> <tbody> <tr> <td>X7T/X7R</td><td style="text-align: center;">无损伤或异常 No defects or abnormalities</td><td style="text-align: center;">目视检查 Visual inspection.</td></tr> </tbody> </table>		类型 Dielectrics	技术要求 Specification	测试条件 Testing Condition	X7T/X7R	无损伤或异常 No defects or abnormalities	目视检查 Visual inspection.																																				
类型 Dielectrics	技术要求 Specification	测试条件 Testing Condition																																									
X7T/X7R	无损伤或异常 No defects or abnormalities	目视检查 Visual inspection.																																									
8.2 尺寸 Dimensions																																											
<table border="1" style="width: 100%; border-collapse: collapse;"> <thead> <tr> <th style="text-align: left;">类型 Dielectrics</th><th style="text-align: center;">技术要求 Specification</th><th style="text-align: center;">测试条件 Testing Condition</th></tr> </thead> <tbody> <tr> <td>X7T/X7R</td><td style="text-align: center;">在要求的范围内 Within the specified dimensions</td><td style="text-align: center;">用千分尺 Using calipers on micrometer</td></tr> </tbody> </table>		类型 Dielectrics	技术要求 Specification	测试条件 Testing Condition	X7T/X7R	在要求的范围内 Within the specified dimensions	用千分尺 Using calipers on micrometer																																				
类型 Dielectrics	技术要求 Specification	测试条件 Testing Condition																																									
X7T/X7R	在要求的范围内 Within the specified dimensions	用千分尺 Using calipers on micrometer																																									
8.3 容量 Capacitance																																											
<table border="1" style="width: 100%; border-collapse: collapse;"> <thead> <tr> <th style="text-align: left;">类型 Dielectrics</th><th style="text-align: center;">技术要求 Specification</th><th style="text-align: center;">测试条件 Testing Condition</th></tr> </thead> <tbody> <tr> <td>X7T/X7R</td><td style="text-align: center;">在要求的容值容差范围内 Within the specified tolerance J: $\pm 5\%$; K: $\pm 10\%$; M: $\pm 20\%$</td><td style="text-align: center;">$1.0 \pm 0.2 \text{VRms}, 1\text{KHz} \pm 10\%$</td></tr> </tbody> </table> <p style="margin-left: 10%;">备注：测试温度：25°C ± 3°C，测试湿度：<70%RH.</p>		类型 Dielectrics	技术要求 Specification	测试条件 Testing Condition	X7T/X7R	在要求的容值容差范围内 Within the specified tolerance J: $\pm 5\%$; K: $\pm 10\%$; M: $\pm 20\%$	$1.0 \pm 0.2 \text{VRms}, 1\text{KHz} \pm 10\%$																																				
类型 Dielectrics	技术要求 Specification	测试条件 Testing Condition																																									
X7T/X7R	在要求的容值容差范围内 Within the specified tolerance J: $\pm 5\%$; K: $\pm 10\%$; M: $\pm 20\%$	$1.0 \pm 0.2 \text{VRms}, 1\text{KHz} \pm 10\%$																																									
8.4 损耗 Dissipation Factor																																											
<table border="1" style="width: 100%; border-collapse: collapse;"> <thead> <tr> <th style="text-align: left;">类型 Dielectrics</th><th style="text-align: center;">技术要求 Specification</th><th style="text-align: center;">测试条件 Testing Condition</th></tr> </thead> <tbody> <tr> <td>X7T/X7R</td><td style="text-align: center;">$DF \leq 2.5\%$</td><td style="text-align: center;">$1.0 \pm 0.2 \text{VRms}, 1\text{KHz} \pm 10\%$</td></tr> </tbody> </table> <p style="margin-left: 10%;">备注：测试温度：25°C ± 3°C，测试湿度：<70%RH.</p>		类型 Dielectrics	技术要求 Specification	测试条件 Testing Condition	X7T/X7R	$DF \leq 2.5\%$	$1.0 \pm 0.2 \text{VRms}, 1\text{KHz} \pm 10\%$																																				
类型 Dielectrics	技术要求 Specification	测试条件 Testing Condition																																									
X7T/X7R	$DF \leq 2.5\%$	$1.0 \pm 0.2 \text{VRms}, 1\text{KHz} \pm 10\%$																																									



潮州三环（集团）股份有限公司

Chaozhou Three-Circle (Group) Co., Ltd.

地址：廣東省潮州市鳳塘三環工業城 郵編(Post Code)：515644

ADD : San Huan Industrial District, Feng Tang Chao Zhou, GuangDong, China

产品标准书 SPECIFICATION FOR APPROVAL	编 号 Document No. DRAAW108E/1-2015
--	---

8.5 绝缘电阻 Insulation Resistance

类型 Dielectrics	技术要求 Specification	测试条件 Testing Condition
X7T/X7R	大于 $4G\Omega$ 或 100s (大于其中较小的数值) More than $4 G\Omega$ or 100s , whichever is smaller.	$U_R \leq 400V$ $U_{测}=U_R$ $U_R > 400V$ $U_{测}=400V$; 充电时间: 60 ± 5 秒 温度: $25^\circ C$ Charge Time: $60 \pm 5sec$ Temperture: $25^\circ C$

备注：测试温度： $25^\circ C \pm 3^\circ C$ ， 测试湿度： $< 70\%RH$.

8.6 耐电压 Dielectric Strength


类型 Dielectrics	额定电压范围 Rated voltage range	耐电压性能测试方法 Measuring Method
X7T/X7R	$100V \leq U_R < 500V$	施加额定电压的 150%, 5 秒, 最大电流不超过 50mA Force 200% Rated voltage for 5second. Max. current should not exceed 50 mA.

8.7 静电容量温度特性 Temperature Coefficient of Capacitance

类型 Dielectrics	技术要求 Specification	测试条件 Testing Condition
X7R	容量变化在 $\pm 15\%$ 以内 Capacitance change within $\pm 15\%$	按系列温度顺序测试电容容量 Measure capacitance under follow table list temperature: 步骤 STEP 1 25 ± 2 2 -55 ± 3 3 25 ± 2 4 125 ± 3 5 25 ± 2
X7T	容量变化在 $+22\%/-33\%$ 以内 Capacitance change within $+22\%/-33\%$	与 $25^\circ C$ 时的电容容量相比较, 电容容量在温度范围内的变化在要求的范围之内。 The ranges of capacitance change compared within the above $25^\circ C$ value over the temperature ranges shall be within the specified ranges.

产品标准书 SPECIFICATION FOR APPROVAL	编 号 Document No. DRAAW108E/1-2015
---	--

8.8 附着力 Adhesion

类型 Dielectrics	技术要求 Specification	测试条件 Testing Condition
X7R/X7T	端电极无松动，也无其它不良现象 No removal of the terminations or other defect shall occur.	施加 6N 的压力，并保持 10±1 秒 The pressurizing force shall be 6N (=600g*f) and the duration of application shall be 10±1sec. 

8.9 可焊性 Solderability of Termination


类型 Dielectrics	技术要求 Specification	测试条件 Testing Condition
X7R/X7T	端电极挂锡面积不小于 95%，针孔或粗糙面积小于 5% 95% min. coverage of both terminal electrodes and less than 5% have pin holes or rough spots.	锡炉温度: 245±5°C 浸入时间: 2±1 秒 两侧端电极完全浸入焊锡炉 Solder temperature: 245±5°C Dipping time: 2±1 seconds. Completely soak both terminal electrodes in solder

产品标准书 SPECIFICATION FOR APPROVAL	编 号 Document No. DRAAW108E/1-2015
---	--

8.10 耐焊性 Resistance to leaching

类型 Dielectrics	技术要求 Specification	测试条件 Testing Condition
X7R/X7T	<p>端电极挂锡面积不小于 95%，针孔或粗糙面积小于 5%，外观无开裂</p> <p>95% min. coverage of both terminal electrodes and less than 5% have pin holes or rough spots.</p> <p>No remarkable visual damage.</p>	<p>预热: 120°C~150°C/60 秒</p> <p>锡炉温度: 270±5°C</p> <p>浸入时间: 10±1 秒</p> <p>两侧端电极完全浸入焊锡炉</p> <p>Solder temperature: 270±5°C</p> <p>preheated: 120°C~150°C/60sec</p> <p>Dipping time: 10±1 seconds.</p> <p>Completely soak both terminal electrodes in solder</p>

8.11 端电极结合强度 Bending

类型 Dielectrics	技术要求 Specification	测试条件 Testing Condition
X7R/X7T	<p>无可见损伤； 容量变化小于等于±10%</p> <p>No remarkable visual damage Cp change ≤ ±10%</p>	<p>将片状电容器安装在测试夹具上，按图所示方向以 1.0mm/s 的速率施加压力，弯曲 1mm。</p> <p>Solder the capacitor on testing substrate and put it on testing stand. The middle part of substrate shall successively be pressurized by pressuring rod at a rated of about 1.0mm/sec. Until the deflection become means of the 1.0mm.</p> 



潮州三环（集团）股份有限公司

Chaozhou Three-Circle (Group) Co., Ltd.

地址：廣東省潮州市鳳塘三環工業城

郵編(Post Code) : 515646

ADD : San Huan Industrial District, Feng Tang Chao Zhou, GuangDong, China

产品标准书 SPECIFICATION FOR APPROVAL	编 号 Document No. DRAAW108E/1-2015
--	--------------------------------------

8.12 耐焊接热 Resistance to Soldering Heat

类型 Dielectrics	技术要求 Specification	测试条件 Testing Condition
X7R/X7T	无明显可见损伤 容量变化在±7.5%以内 DF 满足产品初始值的要求 IR 满足产品初始值的要求 No remarkable visual damage Cp change within ±7.5% DF meets initial standard value. IR meets initial standard value.	焊接温度: 270±5°C 预热: 120~150°C 60 秒 浸入时间: 10±1 秒 在室温下放置 48±4 小时以后测量 试验后在标准条件下恢复 *高介电常数电容器的初始值测量 在 140~150°C 进行 1 小时的热处理后在室温 下放置 48±4 小时 测量初始值 Soldering temperature: 270±5°C Preheating: 120~150°C 60sec. Dipping time: 10±1 seconds. Measurement to be made after being kept at room temperature for 48±4hours. Recovery for the following period under the standard condition after test. *Initial measurement for high dielectric constant type Perform a heat treatment at 140~150°C for 1hr and let sit for 48±4hrs at room temperature. Perform the initial measurement.



潮州三环（集团）股份有限公司

Chaozhou Three-Circle (Group) Co., Ltd.

地址：廣東省潮州市鳳塘三環工業城 郵編(Post Code) : 515646

ADD : San Huan Industrial District, Feng Tang Chao Zhou, GuangDong, China

产品标准书

编 号 Document No.

SPECIFICATION FOR APPROVAL

DRAAW108E/1-2015

8.13 温度快速循环 Temperature Cycle

类型 Dielectrics	技术要求 Specification	测试条件 Testing Condition															
X7R/X7T	<p>无明显可见损伤 容量变化在±7.5%以内</p> <p>No remarkable visual damage Cp change within ±7.5%</p>	<p>按下列步骤进行 5 次循环: To perform 5 cycles of the stated environment</p> <table> <thead> <tr> <th>步 骤 Step</th> <th>温 度 Temperature</th> <th>时 间 Time</th> </tr> </thead> <tbody> <tr> <td>1</td> <td>下限类别温度 +0/-3°C Min. operating Temp.+0/-3°C</td> <td>30min</td> </tr> <tr> <td>2</td> <td>25°C</td> <td>2~3 min</td> </tr> <tr> <td>3</td> <td>上限类别温度 +3/-0°C Max. operating Temp.+3/-0°C</td> <td>30 min</td> </tr> <tr> <td>4</td> <td>25°C</td> <td>2~3 in</td> </tr> </tbody> </table> <p>在室温下放置 48±4 小时以后测量 *高介电常数电容器的初始值测量 在 140~150°C 进行 1 小时的热处理 后在室温下放置 48±4 小时 测量初始值 Measurement to be made after being kept at room temperature for 48±4hrs at room temperature, then measure. *Initial measurement for high dielectric constant type Perform a heat treatment at 140~150 °C for 1hr and let sit for 48±4hrs at room temperature. Perform the initial measurement.</p>	步 骤 Step	温 度 Temperature	时 间 Time	1	下限类别温度 +0/-3°C Min. operating Temp.+0/-3°C	30min	2	25°C	2~3 min	3	上限类别温度 +3/-0°C Max. operating Temp.+3/-0°C	30 min	4	25°C	2~3 in
步 骤 Step	温 度 Temperature	时 间 Time															
1	下限类别温度 +0/-3°C Min. operating Temp.+0/-3°C	30min															
2	25°C	2~3 min															
3	上限类别温度 +3/-0°C Max. operating Temp.+3/-0°C	30 min															
4	25°C	2~3 in															



潮州三环（集团）股份有限公司

Chaozhou Three-Circle (Group) Co., Ltd.

地址：廣東省潮州市鳳塘三環工業城 郵編(Post Code) : 515646

ADD : San Huan Industrial District, Feng Tang Chao Zhou, GuangDong, China

产品标准书

编 号 Document No.

SPECIFICATION FOR APPROVAL

DRAAW108E/1-2015

8.14 稳态湿热 Moisture Resistance ,steady state

类型 Dielectrics	技术要求 Specification	测试条件 Testing Condition
X7R/X7T	<p>外观无明显可见损伤 容量变化在±12.5%以内 DF 为初始值的 2 倍以下 IR:大于 1000MΩ 或 50Ω·F(取较小值)</p> <p>Cp change within ±12.5% DF:Not more than 2 times of initial value $R*C \geq 1000M\Omega$ or $50\Omega \cdot F$, whichever is smaller</p>	<p>测试温度: $40 \pm 2^\circ C$ 湿度: 90~95% RH 测试时间: $500 \pm 12\text{hrs}$</p> <p>在室温下放置 48±4 小时以后测量</p> <p>*高介电常数电容器的初始值测量 在 $140 \sim 150^\circ C$ 进行 1 小时的热处理 后在室温下放置 48±4 小时 测量初始值</p> <p>Test temperature: $40 \pm 2^\circ C$ Humidity: 90~95% RH Testing time: $500 \pm 12\text{hrs}$</p> <p>Measurement to be made after being kept at room temperature for 48±4hrs</p> <p>*Initial measurement for high dielectric constant type Perform a heat treatment at $140 \sim 150^\circ C$ for 1hr and let sit for 48±4hrs at room temperature. Perform the initial measurement.</p>

产品标准书 SPECIFICATION FOR APPROVAL	编 号 Document No. DRAAW108E/1-2015
---	--

9. 产品包装 Packing

9.1 袋式散装 Bulk Packing


10000 个/袋或按客户要求。Standard packing 10Kpcs/bag; others are according to customer request.

9.2 编带式包装 Tape Packing

规格 Type	尺寸 Size (mm)			编带数量(个/盘 pcs/reel)	
	长度 L	宽度 W	厚度 T	纸带 Paper Tape	塑料带 Plastic Tape
1210	3.2	2.5	>1.25	N/A	2,000
1812	4.6	3.2	>1.25	N/A	1000
2220	5.7	5.0	>1.25	N/A	700
2225	5.7	6.4	>1.25	N/A	700

9.2.1 塑料带尺寸

Dimensions of Embossed Packing




A: 2.90 ± 0.20 B: 3.60 ± 0.20 (1210) A: 3.60 ± 0.20 B: 4.90 ± 0.20 (1812)
 A: 5.40 ± 0.20 B: 6.10 ± 0.20 (2220) A: 6.10 ± 0.20 B: 6.80 ± 0.20 (2225)

(单位 unit:毫米 mm)

9.2.2 编带盘尺寸


Dimensions of Reel




产品标准书 SPECIFICATION FOR APPROVAL	编 号 Document No. DRAAW108E/1-2015
---	--

9.2.3 编带方式

Taping Figure




空白部分 Empty section 产品装入部分 Chip insertion section 空白部分 Empty section




(单位 unit: 毫米 mm)

抽出方向 Feeding direction →

产品标准书 SPECIFICATION FOR APPROVAL	编 号 Document No. DRAAW108E/1-2015
<p>9.2.4 编带方法 Taping Method</p> <p>① 包装电容器的编带是顺时针卷绕的，由上往下的方向拉出编带时，传送孔处于编带的右侧。</p> <p>② 在编带的前端，至少留出 5 个间距的引出带。</p> <p>③ 在编带时，必须按下图留出引带部分或空白部分。</p> <p>④ 在盘带的安装中的产品装错的数量每盘必须小于表示数量的 0.1% 或 1 个为限，不连续发生错误。</p> <p>⑤ 上胶带和下胶带不应超出编带的边缘，不能挡住传送孔。</p> <p>⑥ 传送孔的累计误差为 10 个间距：±0.3 毫米以内。</p> <p>⑦ 上胶带的剥离力矩应在 0.1 至 0.6 牛顿以内，其方向如下图所示。</p> <p>① Tapes for capacitors are wound clockwise. The sprocket holes are to the right as the tape is pulled toward the user.</p> <p>② The top tape and base tape are not attached at the end of the tape for a minimum of 5 pitches.</p> <p>③ Part of the leader and part of the empty tape shall be attached to the end of the tape as follows.</p> <p>④ Missing capacitors number within 0.1% of the number per reel or 1pc, whichever is greater, and are not continuous.</p> <p>⑤ The top tape and bottom tape shall not protrude beyond the edges of the tape and shall not cover sprocket holes.</p> <p>⑥ Cumulative tolerance of sprocket holes, 10 pitches: ±0.3mm.</p> <p>⑦ Peeling off force: 0.1 to 0.6N in the direction shown down.</p> 	

产品标准书 SPECIFICATION FOR APPROVAL	编 号 Document No. DRAAW108E/1-2015
---	--

9.2.5 产品标签 Reel Label



标签内容 The Contents of Label

(1) TCC 1812 X7T 224 K 451 G T
 ① ② ③ ④ ⑤ ⑥ ⑦ ⑧

- ①陶瓷电容器代号 Code of Ceramic Capacitor
- ②尺寸 chip size, ③温度特性 dielectrics, ④容量 capacitance, ⑤容量容差 tolerance,
- ⑥额定电压 rated voltage, ⑦厚度 thickness, ⑧包装 packing

- (2) 产品批号 Lot. No.: 004511P214060683800N
- (3) 数量 Qty: 1000pcs
- (4) RoHS:GREEN PARTS 绿色物料

9.2.6.外包装 Package

9.2.6.1 包装箱 Carton

9.2.6.1.1 包装箱尺寸 Carton Size

L	W	H
40cm	36cm	20cm

9.2.6.1.2 数量 Quantity

1 内包装盒=4000PCS 1 INNER BOX=4000PCS

RoHS 标识(根据客户要求张贴) according to customer request

产品 标 准 书 SPECIFICATION FOR APPROVAL	编 号 Document No. DRAAW108E/1-2015
--	--

9.2.6.2 内包装盒 Inner Box

9.2.6.2.1 包装盒尺寸 Size


L	W	H
18.5cm	6.5cm	19cm

9.2.6.2.2 数量: 4Kpcs /盒

1 盘=1000PCS 1 REEL=1,000PCS

1 包装盒=1,000PCS × 4 盘 =4,000PCS 1 INNER BOX=1,000PCS ×4 REEL =4,000PCS

9.2.6.2.3 内包装盒标签 The Label in Inner Box



10.产品禁用物质检验结果 About RoHS

所有产品均符合 RoHS 指令要求

All products accord with RoHS(attached SGS test report)

类别 Sort	检测机构 Test organization	检测报告编号 Report No.	检测日期 Test Date	检测结论 Test Result	有效期限 Expiry
X7T 片式陶瓷电容器 X7T MLCC	SGS	CANEC1320452501	2015-01-23	OK	2016-01-23

必要时可以在产品标签标示 RoHS 标志

Mark RoHS on label of products if necessary

RoHS