




CL 91RW Stainless hot-work steel

Stainless hot-work steel (powder)

CL 91RW is a hard stainless steel with high chrome content. This material is used for production of mould components for high volume injection moulding. Furthermore the material can also be used for stainless functional components with high loads.



CHEMICAL COMPOSITION

Component	Indicative value (%)
Fe	Balance
C	0,03
Si	0,3
Mn	0,3
Cr	12
Ni	9,2
Mo	1,4
Al	1,6



RANGE OF APPLICATION

Tool inserts with conformal cooling for the production of medical or chirurgical instruments as well as for packaging used in food and pharmaceutical industries.

TECHNICAL DATA AFTER RECOMMENDED HEAT TREATMENT

Yield Point R_e^1	approx. 1.600 N/mm ²
Tensile Strength R_m^1	approx. 1.700 N/mm ²
Elongation A ^{1,2}	> 2 %
Young's modulus ³	approx. 200.000 N/mm ²
Thermal conductivity λ^3	approx. 18 W/mK
Hardness ⁴	48 - 50 HRC

¹ Tensile test at 20°C according to DIN EN 50125

² By using a special heat treatment a higher elongation can be achieved.

³ Specification according to the material manufacturer's data sheet.

⁴ Hardness test according to DIN EN ISO 6508

CL 91RW
Stainless
hot-work steel

MICROSECTION

Testpiece (x20 magnification)



Testpiece (x100 magnification)



HEAT TREATMENT

Heat up with 100°C/h to 530°C. Maintain temperature for 4 hours. Allow the components to cool down in the oven with 100°C/h.

MICROSTRUCTURE

Components made from stainless hot-work steel CL 91RW display a homogeneous, dense structure after they are manufactured by means of the metal laser melting process.

EDMIT Industries inc.

1400 Boulevard Ford,
Chateauguay,
Quebec,
Canada, J6J 4Z2

customerservice@edmtinc.com

T: 1-450-691-0111 ext 225

F: 1-855-631-0365

innovation group

All of the specified figures are approximate figures. The figures which are provided reflect the current level of our knowledge and are dependent on process and machine parameters. The information provided on this material data sheet is therefore not binding and is not deemed to be certified.