EJOT Super-SAPHIR® Self-Drilling JT3-3 Range



Ultimate Fastener Tensile Strength



| Fastener Dia | kN |
|--------------|-------|
| 5.5 x L | 11.50 |
| 6.3 x L | 14.17 |
| | |

Ultimate Fastener Shear Strength



| Fastener Dia | kN |
|--------------|-------|
| 5.5 x L | 7.50 |
| 6.3 x L | 12.81 |
| | |

Material Specification

Fastener.

High quality Stainless steel grade 304 St/St, ISO group A2, Din Werkstoff 1.4301.

Drill Point

High quality grade casehardened carbon steel to Din standard 10666.



8mm Hex




Ultimate Pullout Load kN



| Fastener Dia | Nominal Steel Thickness (mm) | | | | | |
|--------------|------------------------------|------|------|------|------|------|
| | 1.20 | 1.40 | 1.60 | 1.80 | 2.50 | 3.00 |
| 5.5 x L | 2.10 | 2.79 | 3.37 | 3.98 | 6.40 | 7.82 |
| 6.3 x L | 3.00 | 3.66 | 4.31 | 4.92 | 7.29 | 8.93 |
| | | | | | | |

Figures based on tests from steel designated as Grade Z35 (BS 2989)

Ultimate Pullover Load kN



| Washer Face | Nominal Sheet Thickness (mm) | | | | | |
|-------------|------------------------------|------|------|-----------|------|--|
| | Steel | | | Aluminium | | |
| | 0.50 | 0.70 | 0.90 | 0.70 | 0.90 | |
| S16 Washer | 4.20 | 5.20 | 5.50 | 2.00 | 2.20 | |
| S19 Washer | 4.50 | 5.65 | 6.00 | 2.40 | 2.90 | |
| | | | | | | |

Figures based on use with R38 profile steel sheets with fastener located in valley of profile and tested in accordance with BS 5427

Figures above are based on results obtained from tests carried out in our Applitec lab in accordance with equipment conforming to BS 5427 on a random sample of fasteners manufactured to EJOT tolerances. Information supplied should form part of a general guide and should performance data for a specific application be required please do not hesitate to contact us.

EJOT UK Limited Sherburn-in-Elmet, Leeds LS25 6PB. Tel: 01977 687040 Fax: 01977 687041 www.ejot.co.uk info@ejot.co.uk

