

Application Guideline for Battery Sealing



1. Recommended ELANTAS Insulation systems

Systems	Distinctive Features
Shimorez SV 400 + Hardener 61	Filled , Acid Resistant, EP System for Battery Terminal Sealing
Shimorez 400 + Hardener 61	Unfilled , Acid Resistant, EP System for Battery lid & Terminal Sealing
Elan-tron MC 19 + W 519	Filled, Acid Resistant, RoHS Compliant, Good Adhesion & Electrical Properties for lid & Terminal Sealing.

2. Application Method: Sealing /Potting

1. Terminal / Lid Sealing(Manual)
2. Terminal / Lid Sealing(Dispensing Machine))

1. Terminal / Lid Sealing (Manual):

- In pre-filled products it is good practice to re-homogenize the material by stirring before use.
- Heat Resin part at 50 – 60 °C under stirring if ambient temperature is below 30°C
- Take Resin component and add proportionate quantity of Hardener and mix carefully till mixture becomes homogenous.
- Avoid air trapping.
- It is advisable to pre-heat the components and /or carry out a de-aeration step under vacuum after potting.
- Follow the suggested curing schedule. (Refer Sr.No-4)

2. Terminal / Lid Sealing (Dispensing Machine):

- In pre-filled products it is good practice to re-homogenize the material by stirring before use.
- Charge Resin & Hardener component on dispensing machine.
- Heat Resin part at 50 – 60 °C under stirring.
- Apply vacuum of 680 mm of Hg for 20 – 30 min to remove traces of moisture & entrapped air.
- It is advisable to pre-heat the components and/or carry out a de-aeration process under vacuum after potting.
- Follow the suggested curing schedule. (Refer Sr.No-4)

3. Known equipment manufacturers



1. HUBERS VM GmbH
 2. Twin Engineers P Ltd, Pune
-

4. Recommended curing schedule:

Systems	Curing Schedule
Shimorez SV 400 + Hard. 61	16 -24 h / 25°C
Shimorez 400 + Hard. 61	25-30 hours at 20°C or 15-20 hours at 30°C or 12-15 hours at 40°C
Elan-tron MC 19 + W 519	15 h / 60 °C

5. Do's:

- Always store the Resin & Hardener under shed as received.
- The Resin & Hardener must be kept away from any exposure to humidity.
- Stir the pre-filled resin part before use.
- Ensure that the lids of resin and Hardener containers are closed tight after use.
- Work place should be clean and well ventilated.
- Workmen should wear protective goggles and gloves.
- Workmen wash their hands with soap & water on completion of job.
- In case of splashes in eyes, wash with plenty of water & take immediately medical help.

Don'ts:

- Avoid storage outside.
- Resin & Hardener should not be stored together.
- Don't keep Resin & Hardener containers open.
- Don't inhale the Hardener.
- Do not eat at work place.

6. Technical Data Sheets (TDS) and Material Safety Data Sheets (MSDS)

TDS & MSDS of relevant products will be available upon request.

7. Company Profile

ELANTAS Beck India Ltd. is a group company of ELANTAS Electrical Insulation Division of ALATNA AG, Germany, an International Specialty Chemical Group currently having 42 operational companies and 46 application and research laboratories worldwide.

In 2006, ELANTAS Beck India completed 50 years of operations in India. The company manufactures a wide range of specialty chemicals for electrical insulation and construction industries. In pursuit of ALATNA's global commitment, ELANTAS Beck India develops new products and processes to meet the changing needs of customers; and utilizes its strengths effectively to be MANUFACTURERS OF RELIABILITY.

Our leadership status ensures we translate our leading technological capabilities and consistent quality standards to the advantage of our customers through contemporary and reliable products and solutions.

Our wide products profile is well supported by comprehensive Technical Service, and an All India Authorised Distributor Network.

ELANTAS Beck India Ltd. has been accredited with the International Quality Management System ISO 9001:2000, Environment Management System Certification ISO 14001:2004 and Occupational Health & Safety Management System BS 18001: 2007.

8. Manufacturing sites in India



Pimpri, Maharashtra



Ankleshwar, Gujarat



ELANTAS Beck India Ltd.

Technical Services:

147, Mumbai-Pune Road, Pimpri, Pune 411018, India
Tel + 91 20 30610 731 / 732. Fax +91 20 30610 880

Regional Sales Offices:

- Bengaluru: Tel: (080) 2528 1649, 2528 3093 Fax: + 91 80 2528 0831
- New Delhi: Tel: (011) 2341 1664, 2341 2940 Fax: + 91 11 2341 3408
- Pune: Tel: (020) 30610800 / 30610672 Fax: + 91 20 30610792
- Kolkata: Tel: (033) 2227 1841 Fax: + 91 33 2227 1843

Head Office & Export:

147, Mumbai Pune Road, Pimpri, Pune 411018, India.
Tel +91 20 30610 800 Fax +91 20 30610 792

www.elantas.com/beck-india