



# Electro-Science Laboratories, Inc.

416 East Church Road • King of Prussia, PA 19406-2625, U.S.A  
610-272-8000 • Fax: 610-272-6759 • www.ElectroScience.com • Sales@ElectroScience.com

## DIELECTRIC COMPOSITION

### 4026-A

ESL 4026-A is a sealing glass designed to match the T.C.E. of 96% alumina and provide high adhesion.

## PASTE DATA

<b>RHEOLOGY:</b>	Thixotropic, screen printable paste
<b>VISCOSITY:</b> (Brookfield RVT, ABZ Spindle, 10 rpm, 25.5°C±0.5°C)	45±15 Pa·s
<b>COLOR:</b>	White/Transparent
<b>SHELF LIFE:</b> (at 25°C)	6 months

## PROCESSING

<b>SCREEN MESH/EMULSION:</b>	325/37.5 µm
<b>LEVELING TIME:</b>	5-10 minutes
<b>DRYING AT 125°C:</b>	10-15 minutes
<b>FIRING TEMPERATURE RANGE:</b>	700°C-730°C
<b>OPTIMUM:</b>	720°C (R.T.C. furnace, 3.5 I.P.M.)
<b>TIME AT PEAK:</b>	8-10 minutes
<b>RATE OF ASCENT/DESCENT:</b>	60°C-100°C/minute
<b>SUBSTRATE FOR CALIBRATION:</b>	96% alumina
<b>THINNER:</b>	ESL 401

4026-A 9408-B

### ESL Affiliates

**Japan:** ESL-Nippon Company, Ltd. • Sukegawa Bldg. • 6<sup>th</sup> floor • 3-4 Yanagibashi 1-chome • Taito-ku • Tokyo 111, Japan • Tel: (011-81)-3-3864-8521 • Fax: (011-81)-3-3864-9270  
NipponSales@ESLNippon.com

**China:** Shanghai Agmet Electro-Science Laboratory Ltd. • Second Floor Bldg. 12A1 • #223 North Fe Te Road • Waigaoqiao Free Trade Zone • Shanghai, China  
Tel: (011-86)-21-5866-0497 • Fax: (011-86)-21-5866-0497 • ShanghaiSales@ShanghaiESL.com

**Europe:** Agmet, Ltd. • 8 Commercial Road • Reading, Berkshire, England RG2 0QZ • Tel: (011-44)-118-987-3139 • Fax: (011-44)-118-986-7331 • Sales@ESLEurope.co.uk

See Caution and Disclaimer on other side.

4026-A 9408-B

---

**CAUTION:** Proper industrial safety precautions should be exercised in using these products. Use with adequate ventilation. Avoid prolonged contact with skin or inhalation of any vapors emitted during use or heating of these compositions. The use of safety eye goggles, gloves or hand protection creams is recommended. Wash hands or skin thoroughly with soap and water after using these products. Do not eat or smoke in areas where these materials are used. Refer to appropriate MSDS sheet.

**DISCLAIMER:** The product information and recommendations contained herein are based on data obtained by tests we believe to be accurate, but the accuracy and completeness thereof is not guaranteed. No warranty is expressed or implied regarding the accuracy of these data, the results obtained from the use hereof, or that any such use will not infringe any patent. Electro-Science assumes no liability for any injury, loss, or damage, direct or consequential arising out of its use by others. This information is furnished upon the condition that the person receiving it shall make their own tests to determine the suitability thereof for their particular use, before using it. User assumes all risk and liability whatsoever in connection with their intended use. Electro-Science's only obligation shall be to replace such quantity of the product proved defective.

---