







Technical Data Sheet

PRODUCT NAME: H5265

DESCRIPTION: Hot Melt Adhesive

SUGGESTED USES: Peelable, Resealable, Pouch Seal Adhesive

CHARACTERISTICS: Pressure Sensitive Hot Melt that provides peelable bond.

The values in this document are preliminary. They may be changed during development work based

on further data.

TECHNICAL PROPERTIES:

Thermosel Viscosity

(Brookfield - ASTM D3236)

Approximately

2235 cPs @ 300 °F (148.9 °C) 1330 cPs @ 325 °F (162.8 °C) 850 cPs @ 350 °F (176.7 °C)

Density

0.95 g/cc @ 77


Typical Viscosity Curve

Temperature (°C)

Softening Point - 172 °F (77.8 °C) Ring and Ball (Herzog - ASTM E28)

Suggested Running

Temperature: 300 - 350 °F (148.9 - 176.7 °C)



2201 North 2nd Street Minneapolis, MN 55411 PHONE - 800.2.GLUE.IT / 612.522.4707

FAX - 800.8.GLUE.IT / 612.529.8645

www.glueit.com

For performance test characteristics please contact your Bostik sales or technical representative.

STORAGE:

Can be stored 730 days in a clean dry place, in its original package at an average temperature of 25°C or below. Storage temperature should not exeed 40°C.

PACKAGING:

For packaging options please call your Bostik sales or technical representative.

SAFETY AND HANDLING:

Clean-up Procedure: Mineral oil or paraffin wax, not to exceed flash point as stated on the MSDS, followed by a thorough purge with the adhesive itself.

Material Safety Data Sheet should be consulted for proper handling before use.

Wear safety gloves and goggles when handling molten adhesive to minimize the risk of burns.

Keep containers covered to minimize contamination.

FDA 21 CFR Numbers

* 175.105

We do not knowingly add any substances derived from animal sources to this product.

Issued 27-Mar-2001 Modified 1 3-May-2005

The information given and recommendations made herein are based on our research and are believed to be accurate, but no guarantee of their accuracy is made. We accept no responsibility for results obtained by the application of this information or the safety and suitability of our products, either alone or in combination with other products. Purchasers are advised to make their own tests to determine whether the product is suitable for their purposes under their own operating conditions. Unless otherwise agreed to in writing, we sell the products without warranty as to merchantability and Fitness for a particular purpose or any other warranty, expressed or implied, AND buyers and users assume all responsibility and liability for loss or damage arising from the handling and use of our products. Nothing contained herein shall be construed to imply the nonexistence of any relevant patents or to constitute permission, inducement or recommendation to practice any invention covered by any patent, without authority from the owner of the patent.

Bostik, Inc. 11320 Watertown Plank Road Wauwatosa, WI 53226-3434

Telephone: 414-774-2250 Fax: 414-774-8075

Specific limitation(s) apply. Please consult the specific FDA regulation or contact Bostik, Inc. for more information.