

Technical Data Sheet

Product #HM216-LM

Applications:	Case and carton sealing
General Information:	HM216-LM was formulated for premium low melt packaging applications. Low odor, non-stringing, bonds well to recycled board stocks.
Recommended Application Temp.:	250°F – 275°F
Specifications:	
Color:	Opaque white
Viscosity:	1000 @ 250°F
Speed of Set:	Fast
Open Time:	Short
Softening Point:	159°F
Heat Stability:	No Skin, Gel, or Char (96 Hours @ 350°F)
Tack:	Aggressive
Packaging:	Slats, 50lb. boxes, 30 boxes per skid or bulk super sacks (approx. 1500 lbs.)

*Note: components contained in this product conform to FDA regulations 21 CFR 175.105 concerned with food packaging materials.

**Note: The date presented is based upon tests believed to be reliable. However, manufacturer does not guarantee its accuracy or completeness. Manufacturer will assume no responsibility for results obtained or for incidental or consequential damages arising from the use of this data. Customer is responsible for determining suitability of this product for his needs.

The buyer should conduct its own tests of this product before use to determine proper preparation technique and suitability for proposed application. American Chemical, Inc. warrants that the product conforms with American Chemical, Inc. written specifications, and is free from defects. American Chemical, Inc. disclaims all other warranties, expressed or implied, including the warranties of merchantability and fitness for a particular purpose. The buyer's sole remedy for non compliance with this warranty shall be for the replacement of the product or refund of the buyer's purchase price.

7/2008