

Diamond Drill Bit Mold Materials

World Renowned Graphite Expertise and Service

GrafTech is the world leader in Diamond Drill Bit (DDB) mold components, offering the technical support, service and global reach required in this demanding application. GrafTech has years of machining expertise for DDB mold components, and GrafTech's consistent reliability has been proven throughout the years.



Features

- High thermal shock resistance
- Strength increases with temperature
- Performs at high temperatures
- Superior oxidation resistance

Benefits

- Global reach
- Local machining
- Unmatched expertise and service
- Broad size range of graphite



Typical Properties at Room Temperature*

DBX™ Graphite

Characteristic	Unit	WG	AG	Unit	WG	AG
Density	lbs/ft ³	108		g/cm ³	1.73	
Maximum Particle Size	inches	0.030		mm	0.76	
Specific Resistance	10 ⁻⁴ Ω in	2.7	3.5	μΩm	6.5	9.0
Flexural Strength: 4-point bending	psi	3200	2400	MPa	22	16
Young's Modulus	10 ⁶ psi	1.5	1.3	GPa	10	8.9
Tensile Strength	psi	2300	1700	MPa	15	12
Compressive Strength	psi	6600	6600	MPa	46	46
C.T.E. (RT to 100 °C)	10 ⁻⁶ /°F	1.4	2.0	10 ⁻⁶ /°C	2.5	3.5
Hardness	Rockwell "R"	83		Rockwell "R"	83	
Porosity	%	14		%	14	
Thermal Conductivity	BTU-ft/hr ft ² °F	100	85	W/mK	175	150
Ash Content	%	0.12		%	0.12	

DBZ™ Graphite

Characteristic	Unit	WG	AG	Unit	WG	AG
Density	lbs/ft ³	103		g/cm ³	1.65	
Maximum Particle Size	inches	0.030		mm	0.76	
Specific Resistance	10 ⁻⁴ Ω in	2.8	3.6	μΩm	6.8	9.4
Flexural Strength: 4-point bending	psi	2400	1900	MPa	17	13
Young's Modulus	10 ⁶ psi	1.4	1.0	GPa	9.6	7.5
Tensile Strength	psi	2000	1300	MPa	13	8.9
Compressive Strength	psi	6600	6600	MPa	46	46
C.T.E. (RT to 100 °C)	10 ⁻⁶ /°F	1.4	2.0	10 ⁻⁶ /°C	2.5	3.5
Hardness	Rockwell "R"	70		Rockwell "R"	70	
Porosity	%	18		%	18	
Thermal Conductivity	BTU-ft/hr ft ² °F	95	80	W/mK	145	130
Ash Content	%	0.12		%	0.12	

* Properties listed are typical and cannot be used as accept/reject specifications

Our global team of Applications Engineers are knowledgeable about graphite and applications spanning multiple industries. These include metallurgical casting, electronics, chemical, nuclear, defense/aerospace, solar, LED, semiconductor, and other high temperature processes.

Regardless of your product design phase (concept, prototyping, or mass production), we offer technical answers to some of your most challenging problems with a fast response time.



Please contact a GrafTech Applications Engineer today at applicationsengineering@graftech.com

www.graftech.com | grafstar@graftech.com

United States of America
101 N. Philippi Pike
Annoore, WV 26323-0120
Ph: +1-800-842-8805
+1-304-624-1253

China
Unit 2104 of International Capital Plaza
1318, Sichuan Road North
Hongkou District, Shanghai China
Ph: +86-21-6325-8018

Italy
Via Forno Allione, 2
1-25040 Malonno, Brescia, Italy
Ph: +39-036-463-0131

France
La Lechere
73264 Aigueblanche Cedex, France
Ph: +33-04-79-41-45-00

© 2011 GrafTech International Holdings Inc. This information is based on data believed to be reliable but GrafTech makes no warranties, express or implied, as to its accuracy and assumes no liability arising out of its use. The data listed falls within the normal range of product properties but should not be used to establish specification limits or used alone as the basis of design. GrafTech's liability to purchasers is expressly limited to the terms and conditions of sale. GRAFSTAR, DBX and DBZ are trademarks of GrafTech International Holdings Inc.

Redefining limits