

CHV Graphite

Technical Data Sheet 5076

Product Overview

GRAFSTAR™ CHV graphite is an extension of CS graphite in a 22" x 48" (559 x 1200 mm) cross section. CHV graphite has excellent thermal shock resistance, based on thermal expansion and thermal conductivity characteristics. CHV graphite is ideal in high temperature applications requiring larger sizes.

Applications

- Induction and vacuum furnace parts
- Pressure casting molds
- Composite tooling and carbon/carbon parts

Sizes

- 559 x 1200 x 3000 mm rectangles
- 22" x 48" x 120" rectangles

Typical Properties at Room Temperature*

Characteristic	Unit	WG	AG	Unit	WG	AG	Unit	WG	AG
Density	lbs/ft ³	110		g/cm ³	1.76		g/cm ³	1.76	
Maximum Particle Size	inches	0.060		mm	1.52		mm	1.52	
Specific Resistance	10 ⁻⁶ Ωin	3.6	5.2	μΩm	9.1	13.2	μΩm	9.1	13.2
Flexural Strength	psi	1900	1500	kg/cm ²	133	105	MPa	13	10
Young's Modulus	10 ⁶ psi	1.46	0.97	kg/mm ²	1024	682	GPa	10.1	6.7
Tensile Strength	psi	1100	1050	kg/cm ²	77	74	MPa	8	7
Compressive Strength	psi	3850	4200	kg/cm ²	270	294	MPa	27	29
Permeability	Darcy	0.17	0.09	Darcy	0.17	0.09	Darcy	0.17	0.09
Hardness	Shore	22		Shore	22		Shore	22	
C.T.E. (to 100 °C)	10 ⁻⁶ /°F	0.8	1.5	10 ⁻⁶ /°K	1.4	2.7	10 ⁻⁶ /°K	1.4	2.7
Thermal Conductivity	BTU-ft/hr ft ² °F	80	60	W/mK	139	104	W/mK	139	104
Ash Content	%	1.3		%	1.3		%	1.3	

Notes:

* Properties listed are typical and cannot be used as accept/reject specifications

www.graftech.com | grafstar@graftech.com

Redefining limits

United States of America

101 N. Phillippi Pike
Anmoore, WV 26323-0120
Ph: +1-800-842-8805
+1-304-624-1253

China

Unit 2104 of International Capital Plaza
1318, Sichuan Road North
Hongkou District, Shanghai China
Ph: +86-21-6325-8018

Italy

Via Forno Allione, 2
1-25040 Malonno, Brescia, Italy
Ph: +39-036-463-0131

France

La Lechere
73264 Aigueblanche Cedex, France
Ph: +33-4-79-41-45-00