

ISO 9001 Registered

121 Tech Drive Sanford, FL 32771 (407) 322-4000 Fax: (407) 321-9700 www.hernonmfg.com

# Technical Data Sheet EF<sup>®</sup> Activator 47

Page 1 of 1

# Product Description

December 2009

Hernon<sup>®</sup> Environmental Friendly<sup>®</sup> (EF<sup>®</sup>) Activator 47 is solvent free and environmentally friendly. This activator is designed to initiate the cure of Hernon<sup>®</sup> toughened acrylic adhesives

Since **EF**<sup>®</sup> **Activator 47** contains no solvents, no waiting time for solvent evaporation is needed prior to assembly.

# **Typical Properties**

Property	Value
Appearance	Light amber liquid
Specific Gravity @ 25°C	1.10
Viscosity @ 25°C, cP	15
Drying Time	None
On Part Life, hours	2
Flash Point	See MSDS

## **Typical Curing Performance**

The fixture time for **Hernon**<sup>®</sup> **Adhesives** with **EF**<sup>®</sup> **Activator 47** is between 16 and 60 seconds with full cure obtained within 24 hours.

These times are based on specific bond line gaps and adhesive viscosity. All applications should be evaluated for actual fixture time before repeated use or establishing automated assembly procedures.

An increased bond line thickness may decrease strength and will increase fixture time.

## **General Information**

This product is not recommended for use in pure oxygen and/or oxygen rich systems and should not be selected as a sealant for chlorine or other strong oxidizing materials.

For safe handling information on this product, consult the Material Safety Data Sheet (MSDS).

#### Never Mix Activator and Adhesive directly in bulk.

Where aqueous washing systems are used to clean the surfaces before bonding, it is important to check for compatibility of the washing solution with the adhesive. In some cases these aqueous washes can affect the cue and performance of the adhesive.

### **Directions For Use**

For best results apply a thin layer of **EF**<sup>®</sup> **Activator 47**. Parts must remain immobilized following assembly until fixtured. This assures development of maximum bond strength.

If adhesive is applied directly over activator, parts should be assembled without delay since curing begins immediately. Reduced bond strength may be obtained with too much activator.

Activator can be easily applied with a mist sprayer for automated assembly. Swabbing or transfer pad printing is also acceptable. Natrual felt or open-cell monomer resistant polyurethane foams are suitable.

#### Cleanup

Excess activator and adhesive may be cleaned up with alcohol or acetate solvents.

Avoid skin and eye contact. Non-porous protective gloves or barrier hand cream should be used. Do not wear jewelry. Protective eye goggles should be worn when handling activator.

Use positive ventilation to remove vapors.

#### Storage

**EF**<sup>®</sup> **Activator 47** should be stored in a cool, dry location in unopened containers at a temperature between 46°F to 82°F (8°C to 28°C) unless otherwise labeled. Optimal storage is at the lower half of this temperature range. To prevent contamination of unused material, do not return any material to its original container.

#### **Dispensing Equipment**

**Hernon**<sup>®</sup> offers a complete line of semi and fully automated dispensing equipment. Contact **Hernon**<sup>®</sup> **Sales** for additional information.

These suggestions and data are based on information we believe to be reliable and accurate, but no guarantee of their accuracy is made. HERNON MANUFACTURING<sup>®</sup>, INC. shall not be liable for any damage, loss or injury, direct or consequential arising out of the use or the inability to use the product. In every case, we urge and recommend that purchasers, before using any product in full scale production, make their own tests to determine whether the product is of satisfactory quality and suitability for their operations, and the user assumes all risk and liability whatsoever, in connection therewith. Hernon's Quality Management System for the design and manufacture of high performance adhesives and sealants is registered to the ISO9001 Quality Standard.