

Technical Data Sheet Silastomer[®] 340

September 2012

Page 1 of 1

Product Description

Hernon[®] Silastomer[®] 340 is a one-component, moisture curing RTV (room temperature vulcanizing) ready-to-use adhesive / sealant and gasketing compound.

Can be used as a form in place gasket material where temperatures may reach up to 600°F. **Silastomer[®] 340** will remain flexible with excellent resistance to aging and vibration. Meets MIL-46106 Type 1 requirements. Also FDA compliant with Regulation Title 21 CFR 175.105 where incidental food contact may be involved.

Typical uses are to replace conventional paper and cork gaskets in:

Automotive

- Valve Covers
- Axle housings
- Water and oil pump seals
- Thermostat housings
- Timing chain covers
- Solenoid covers

Commercial

- Pump and compressor gaskets
- Air conditioning gaskets
- Ductwork gaskets
- Wire and cable insulation

Typical Properties (Uncured)

Property	Value
Base	Polysiloxane
Color	Red
Viscosity	Thixotropic Paste
Specific Gravity	1.18
Extrusion Rate, 0.125 in. Orifice, 90 psi air pressure	250-500 gm/min
Application Temperature Range (uncured)	0 to +120°F
Flash Point	See MSDS

Directions for Use

Surfaces should be clean and dry. Recommend cleaning surface with a solvent like Mineral Spirits. For gasket applications, apply an even bead to one surface.

Surround all bolt holes. Press parts together, and torque normally. On surfaces where adhesion is not required, a light coat of oil or grease will aid in releasing the parts. Not recommended for cylinder heads, manifolds or in contact with fuels.

To remove – can be wiped off parts before cured. After material cures, abrade or scrape from the surface.

Typical Properties (Cured)

Physical Properties

Property	Value
Gap Cure, in. (mm)	0.25 (6)
Tack Free Time at 77°F, minutes	10
Full Cure at 77°F, 0.25 in. bead, hours	24
Peel Strength Alum/SS, ppi	≥ 15
Hardness, Shore A	18 - 25
Tensile Strength at Break, psi	≥ 150
Elongation, %	≥ 400
Operating Temperature Range, °F	-70 to 600°F

General Information

This product is not recommended for use in pure oxygen and/or oxygen rich systems and should not be selected as a sealant for chlorine or other strong oxidizing materials.

For safe handling information on this product, consult the Material Safety Data Sheet (MSDS).

Storage

Silastomer[®] 340 should be stored in a cool, dry location in unopened containers at a temperature between 46°F to 85°F unless otherwise labeled. To prevent contamination of unused material, do not return any material to its original container.

Dispensing Equipment

Hernon[®] offers a complete line of semi and fully automated dispensing equipment. Contact **Hernon[®] Sales** for additional information.

These suggestions and data are based on information we believe to be reliable and accurate, but no guarantee of their accuracy is made. HERNON MANUFACTURING[®], INC. shall not be liable for any damage, loss or injury, direct or consequential arising out of the use or the inability to use the product. In every case, we urge and recommend that purchasers, before using any product in full scale production, make their own tests to determine whether the product is of satisfactory quality and suitability for their operations, and the user assumes all risk and liability whatsoever, in connection therewith. Hernon's Quality Management System for the design and manufacture of high performance adhesives and sealants is registered to the ISO 9001:2008 Quality Standard.