



BQF09 Qualatrile Blue Nitrile 9" Powder-Free Gloves

ESD Technical Bulletin



Electrostatic Decay in Combination with a Person

Standard: Rate of decay shall be less than 2.0 sec-

onds @12%RH

+1kV to -100V Ave: 0.318 sec. -1kV to

-100V Ave: 0.312 sec.

Method: Mil-STD-3010C, 4046 (Modified)

@49.5%RH

Café Glove Resistance in Combination with a Person

Target: Less than 1.0 x 10¹¹ ohms @ 12%RH

and 50%RH

Range: Min: 1.5×10^9 ohms

Max: 6.7 x 109 ohms

Method: ANSI/ESD SP15.1 @49.5%RH for 48

Hours

ESD Inside Shelf Life

Requirement: 5 Years

Found: Indefinite for Storage **Reference:** Contains no Antistats

Surface Resistance

Target: 1.0×10^{11} ohms and greater at 12%RH

Range: Min: 8.3 x 10⁸ ohms Max: 2.9 x 10⁹ ohms

Method: ANSI/ESD STM11.11-2015 @

49.5%RH for 48 Hours

Volume Resistance

Standard: Less than 1.0 x 10¹¹ ohms @12%RH

Range: Min: 1.8 x 10⁸ ohms Max: 2.5 x 10⁸ ohms

Method: ANSI/ESD STM11.12-2015 @ 49.5%RH

for 48 Hours

ev: 28Sept2016

Product Recommendations: The information presented herein is not guaranteed in any way, although to the best of QRP's knowledge and belief, it is true and accurate as of this date. Because the manner and conditions of use, handling, storage and other factors may involve a variety of safety, performance, or regulatory considerations unknown to QRP, users are responsible for determining the suitability of any QRP product for their specific purpose. QRP, Inc. does not warrant the results to be obtained in using any QRP product, and disclaims all liability with respect to the use, handling or further processing of any such product.