



# 8BQF09 Qualatrile Blue Nitrile 9" Powder-Free Gloves

## **ESD Technical Bulletin**



## Electrostatic Decay in Combination with a Person

Rate of decay shall be less than 2.0 sec-Standard:

onds @12%RH

+1kV to -100V Ave: 0.502 sec. -1kV to Found:

-100V Ave: 0.459 sec.

Mil-STD-3010C, 4046 (Modified) Method:

@49.5%RH

## Café Glove Resistance in Combination with a Person

Less than 1.0 x 1011 ohms @ 12%RH Target:

and 50%RH

Min: 1.2 x 10<sup>9</sup> ohms Range:

Max: 7.0 x 109 ohms

ANSI/ESD SP15.1 @ 49.5%RH for 48 Method:

Hours

### **ESD Inside Shelf Life**

**Requirement:** 5 Years

Found: Indefinite for Storage

Reference: Contains no Antistats

#### **Surface Resistance**

1.0 x 10<sup>11</sup> ohms and greater at 12%RH **Target:** 

Min: 2.4 x 10<sup>10</sup> ohms Range:

Max: 1.1 x 1011 ohms

ANSI/ESD STM11.11-2015 @ Method:

49.5%RH for 48 Hours

#### **Volume Resistance**

Standard: Less than 1.0 x 1011 ohms @12%RH Min: 5.7x 109 ohms

Range:

Max: 1.2 x 1010 ohms

ANSI/ESD STM11.12-2015 @ 49.5%RH Method:

for 48 Hours

Product Recommendations: The information presented herein is not guaranteed in any way, although to the best of QRP's knowledge and belief, it is true and accurate as of this date. Because the manner and conditions of use, handling, storage and other factors may involve a variety of safety, performance, or regulatory considerations unknown to QRP, users are responsible for determining the suitability of any QRP product for their specific purpose. QRP, Inc. does not warrant the results to be obtained in using any QRP product, and disclaims all liability with respect to the use, handling or further processing of any such product.

rev: 28Sept2016