

SUBMITTAL SHEET (effective 06/15/07)

Polymer Base: Neoprene, EPDM, SBR Blend

F-05011 (Black)

Physical Properties	Unit	Test Method	Typical Results
Density	g/cm ³	ASTM D 1056	0.144 ± 0.032
	lb/ft ³	ASTM D 1056	9 ± 2
Hardness, Durometer Shore 00		ASTM D 2240	45 ± 5
Compression Deflection (25%)	kPa	ASTM D 1056	24 ± 10
	psi	ASTM D 1056	3.5 ± 1.5
Compression Set	%	ASTM D 1056	≤ 30%
Tensile Strength	kPa	ASTM D 412 (Die A)	690
	psi	ASTM D 412 (Die A)	100
Tear Strength	kN/m	ASTM D 624 (Die C)	2.8
	lb/in	ASTM D 624 (Die C)	12
Elongation	%	ASTM D 412 (Die A)	150%
Resilience	%	ASTM D 2632	30%
Service Temperature			
Low	°F	ASTM D 746	-40
High Continuous	°F	ASTM D 746	200
High Intermittent	°F	ASTM D 746	250
Water Absorption			
Maximum Weight Change	%	ASTM D 1056	< 5%
Fluid Immersion (7 days at 23 °C [73.4 °F])			
ASTM Ref. Fuel B, Weight Change (%)	%	ASTM D 1056	Not Applicable
Accelerated Aging (7 days at 70 °C [158 °F])			
Flexibility (180° bend without cracking)		ASTM D 1056	Pass
Appearance change		ASTM D 1056	None
Change in Compression Deflection	%	ASTM D 1056	± 30%
Combustion Characteristics			
		FMVSS-302	Pass
		UL 94HF-1	Pass
			UL Listed (black & gray)

ASTM D 1056 designation: **2A1**
 SAE J 18 APR2002 designation: **2A1**
 ASTM D 6576: **II-A/B/C Soft**

For updates to this document please refer to our website.

Armacell provides this information as a technical service. To the extent the information is derived from sources other than Armacell, Armacell is substantially, if not wholly, relying upon the other source(s) to provide accurate information. Information provided as a result of Armacell's own technical analysis and testing is accurate to the extent of our knowledge and ability, using effective standardized methods and procedures. Each user of these products, or information, should perform their own tests to determine the safety, fitness and suitability of the products, or combination of products, for any foreseeable purposes, applications and uses by the user and by any third party to which the user may convey the products. Since Armacell cannot control the end use of this product, Armacell does not guarantee that the user will obtain the same results as published in this document. The data and information is provided as a technical service, and the data and information are subject to change without notice.



Seal & Design
Able Division
 5533 Steeles Avenue West Unit 11
 Toronto, Ontario M9L 1S7
 Ph: (416) 741-0750
 Gasket@AbleSealAndDesign.com

Seal & Design
Corporate Headquarters
 4015 Casilio Parkway
 Clarence, NY 14031
 Ph: (716) 759-2222
 Info@SealAndDesign.com
 www.SealAndDesign.com

Seal & Design
Higbee Division
 6741 Thompson Rd N
 Syracuse, NY 13221
 Ph: (315) 432-8021
 Sales@Higbee-Inc.com