



an EnPro Industries company

Garlock BLUE GYLON[®] 3505 BLUE GYLON For Oxygen Service

MATERIAL PROPERTIES

Color: Blue

Composition: PTFE with Aluminosilicate microspheres

Fluid Services¹: Oxygen service, moderate concentrations of acids and caustics,

solvents, refrigerants, cryogenics, hydrocarbons and hydrogen peroxide

Temperature², °F (°C)

Minimum: -450 (-268)
Continuous Max: +500 (+260) **Pressure²**, Maximum, psig (bar): 800 (55)

P x T (max.)², psig x °F (bar x °C)

1/32 and 1/16": 350,000 (12,000) 1/8": 250,000 (8,600) Flammability: Will Not Burn Bacterial Growth: Will Not Support

Meets Specification: NSF 61 (National Sanitation Foundation), FDA (Food and Drug

Administration) and USP Class VI (US Pharmacopeia)

TYPICAL PHYSICAL PROPERTIES

ASTM F36	Compressibility, %:	25-45
ASTM F36	Recovery, %:	30
ASTM F38	Creep Relaxation, %:	40.0
ASTM F152	Tensile, Across Grain, psi (N/mm²):	2000 (13.8)
ASTM D792	Specific Gravity:	1.70
ASTM D1708	Modulus @ 100% Elongation, psi (N/mm2):	1500 (10.3)
ASTM F433	Thermal Conductivity (K), W/m°K (Btu.·in./hr.·ft.²·°F):	0.14-0.24 (1.00-1.65)
ASTM D149	Dielectric Properties, range, volts/mil.	
	Sample conditioning	<u>1/16"</u>
	3 hours at 250°F:	318 -
	96 hours at 100% Relative Humidity	245 -
ASTM F586	Design Factors	<u>1/16" & Under</u> <u>1/8"</u>
	"m" factor:	3.0 2.5
	"y" factor, psi (N/mm²):	1650 (11.4) 3000 (20.7)
ASTM F104	Line Call Out:	F456999A9B7E99K3M6 ⁽³⁾

SEALING CHARACTERISTICS

	ASTM F37B	DIN 3535- 4
	Fuel A	Gas Permeability
Gasket Load, psi (N/mm2):	1000 (7)	4640 (32)
Internal Pressure, psig (bar):	9.8 (0.7)	580 (40)
Leakage	0.12 ml/hr.	<0.015 cc/min

Notes

This is a general guide and should not be the sole means of selecting or rejecting this material. ASTM test results in accordance with ASTM F-104; properties based on 1/32" (0.8mm) sheet thickness unless otherwise mentioned.

Seal & Design Able Division

5533 Steeles Avenue West Unit 11 Toronto, Ontario M9L 1S7 Ph: (416) 741-0750 Gasket@AbleSealAndDesign.com

Seal & Design Corporate Headquarters

4015 Casilio Parkway Clarence, NY 14031 Ph: (716) 759-2222 Info@SealAndDesign.com www.SealAndDesign.com

Seal & Design Higbee Division

6741 Thompson Rd N Syracuse, NY 13221 Ph: (315) 432-8021 Sales@Higbee-Inc.com

^{*} Values do not constitute specification Limits

¹ See Garlock chemical resistance guide.

² Based on ANSI RF flanges at our preferred torque. When approaching maximum pressure, continuous operating temperature, minimum temperature or 50% of maximum PxT, consult Garlock Applications Engineering.

³ Increase in IRM Oil #903 (fourth numeral 9 is thickness, fifth numeral 9 is weight): Thickness = 1.0% max, Weight = 2.0% max. Sixth numberal 9: % Increase in Water: Weight = 1.0% max. A9: Leakage in Fuel A (Isooctane), Pressure = 9.8psig (0.7bar), Gasket Load = 1,000psi (7.0N/mm2): Typical = 0.12ml/hr, Max = 1.0ml/hr. E99: % Increase in ASTM Fuel B: Weight: 2.0% max., Thickness: 1.0% max.