CHEMINAX

100 OHMS, AWG 26, 19 STRANDS OF AWG 38, TWIN CONDUCTOR CABLE, OUTER SPACE

Date: 12-13-06


0026A0664

Revision:

THIS SPECIFICATION SHEET FORMS A PART OF THE LATEST ISSUE OF RAYCHEM SPECIFICATION 1200.

CONSTRUCTION **DETAILS**

DIMENSIONS ARE NOMINAL VALUES IN INCHES UNLESS OTHERWISE DESIGNATED.



CONDUCTOR

AWG 26, 19 Strands of AWG 38, Silver-Coated High Strength Copper

DIELECTRIC

Radiation-crosslinked Modified ETFE (Dual Extruded) Color - Light Blue/White

SHIELD

AWG 38 Tin-Coated Copper

JACKET

Radiation-Crosslinked Modified ETFE

Outer jacket color will be white (designated by a "-9" appended to the part number, e.g. 0026A0664-9) unless otherwise specified.

Designate outer jacket color with a dash number in accordance with MIL-STD-681. Other codes and suffixes may be added to the part number, as necessary, to capture any additional requirements imposed by the purchase order.

ELECTRICAL CHARACTERISTICS

CHARACTERISTIC IMPEDANCE 100 ± 10 ohms, Method D at 1 MHz

CAPACITANCE - MUTUAL 16.0 pF/ft. (nominal)

ADDITIONAL REQUIREMENTS

COMPONENT WIRE PRIOR TO CABLING (Test Procedures per SAE AS22759)

CROSSLINK PROOF $300 \pm 3^{\circ}$ C for 1 hour, .750 inch mandrel,

LOW TEMPERATURE -65 ± 2°C for 4 hours, .500 inch mandrel,

COLD BEND .500 lb., 2.5 kV dielectric test

SHRINKAGE $200 \pm 3^{\circ}$ C for 1 hours,

.125 inch (maximum) in 12 inches 5000 megohms for 1000 ft. (minimum)

.625 lb., 2.5 kV dielectric test

INSULATION RESISTANCE INSULATION (DIELECTRIC)

(total insulation)

TENSILE STRENGTH 5000 lbf/in² (minimum) **ELONGATION** 50% (minimum)

INSULATION FLAWS

SPARK TEST 3.0 kV (rms) IMPULSE TEST 8.0 kV (peak)

FINISHED CABLE (Test Procedures per NEMA WC27500)

BLOCKING 200°C for 6 hours

LOW TEMPERATURE -55 ± 5°C for 4 hours, 6.0 inch mandrel

COLD BEND

CROSSLINKED VERIFICATION 300 ± 5°C for 6 hours, 6.0 inch mandrel **FLAMMABILITY** 3 seconds (maximum); 3.0 inches (Method B of Spec 1200) (maximum), no flaming of facial tissue

JACKET FLAWS

SPARK TEST 1.0 kV (rms) IMPULSE TEST 6.0 kV (peak)

JACKET

TENSILE STRENGTH 5000 lbf/in2 (minimum) **ELONGATION** 50% (minimum) .005 (minimum) JACKET THICKNESS

.008 (nominal)

SHIELD COVERAGE 90% (minimum) **VOLTAGE WITHSTAND** 1500 volts (rms)

(DIELECTRIC)

WEIGHT 14.6 lbs/1000 ft. (nominal)

OUTER SPACE REQUIREMENTS

RADIATION RESISTANCE 500 megarads/4.50 inch mandrel

VACUUM STABILITY

TOTAL MASS LOSS (TML) 1.0% (maximum) VOLATILE CONDENSABLE 0.1% (maximum)

MATERIAL (VCM)

WEIGHT LOSS: (Test per Spec 55/) 0.45% (maximum)

Users should evaluate the suitability of this product for their application. Specifications are subject to change without notice.
Tyco Electronics also reserves the right to make changes in materials or processing, which do not affect compliance with any specification, without notification to Buyer.



.137

.153

