SPECIFICATION CONTROL DRAWING

55PC0814

WIRE, RADIATION-CROSSLINKED, MODIFIED, ETFE-INSULATED, GENERAL PURPOSE. NORMAL AIRFRAME


07-15-04

Date

Revision

Α

This specification sheet forms a part of the latest issue of Raychem Specifiction 55PC.



| CONSTRUCTION DETAILS | | | | | | | | | | | |
|----------------------|-----------------------|--|---------------------------|-----------------|------------------------|---|---------------------|-----------------|---------------------|------------------|---------------------|
| PART NUMBER 1/ | WIRE SIZE (AWG) | CONDUCTOR STRANDING (number x AWG) | CONDUCTOR DIAMETER (in.) | | | FINISHED WIRE | | | | | |
| | | | | | | MAXIMUM | DIAMETER | | | WEIGHT | |
| | | | LOWER SPEC LIMIT | TARGET VALUE | UPPER SPEC LIMIT | RESISTANCE AT 20°C (ohms/1000ft.) | (in.) | | | (lbs/1000 ft.) | |
| | | | | | | | LOWER SPEC LIMIT | TARGET VALUE | UPPER SPEC LIMIT | TARGET VALUE | UPPER SPEC LIMIT |
| 55PC0814-26-* | 26 | 19 x 38 | .0175 | .0183 | .0191 | 44.8 | .0366 | .0385 | .0404 | 1.55 | 1.70 |
| 55PC0814-24-* | 24 | 19 x 36 | .0225 | .0233 | .0241 | 28.4 | .0416 | .0435 | .0454 | 2.18 | 2.34 |
| 55PC0814-22-* | 22 | 19 x 34 | .0285 | .0293 | .0301 | 17.5 | .0476 | .0495 | .0514 | 3.12 | 3.30 |
| 55PC0814-20-* | 20 | 19 x 32 | .0365 | .0375 | .0385 | 10.7 | .0561 | .0580 | .0599 | 4.64 | 4.85 |
| 55PC0814-18-* | 18 | 19 x 30 | .0452 | .0464 | .0476 | 6.8 | .0659 | .0680 | .0701 | 6.94 | 7.27 |
| 55PC0814-16-* | 16 | 19 x 29 | .0514 | .0527 | .0538 | 5.3 | .0737 | .0760 | .0783 | 8.80 | 9.17 |

WIRE RATINGS AND ADDITIONAL REQUIREMENTS

TEMPERATURE RATING: 200°C

Maximum continuous conductor temperature

VOLTAGE RATING: 600 volts (rms) at sea level

COLOR: White preferred

CROSSLINK VERIFICATION: 300 ± 3°C for 1 hour IDENTIFICATION AND COLOR STRIPING DURABILITY: 125 cycles (250 strokes) (minimum), 500 g weight INSULATION ELONGATION AND TENSILE STRENGTH:

Total Insulation.

Elongation, 50% (minimum)

Tensil Strength, 5000 lbf/in² (minimum)

INSULATION FLAWS:

Spark Test, 3.0 kV (rms)

Impulse Dielectric Test, 8.0 kV (peak)

 $INSULATION\ THICKNESS:\ .010\ in.\ (nominal)\ total\ insulation\\ SHRINKAGE:\ 230\pm3^{\circ}C\ for\ 1\ hour,\ 0.125\ in.\ (maximum)\ in\ 12\ in.$

VOLTAGE WITHSTAND TEST (POST ENVIRONMENTAL):

2500 volts (rms)

PART NUMBER:

The "*" in the part numbers above shall be replaced by color code designators.

1/ Example: AWG 22, white: 55PC0814-22-9

AWG 22, white with black stripe: 55PC0814-22-90

Users should evaluate the suitability of this product for their application. Specifications are subject to change without notice.

Tyco Electronics also reserves the right to make changes in materials or processing, which do not affect compliance with any specification, without notification to Buyer.

1/ COLORS AND COLOR CODE DESIGNATORS SHALL BE IN ACCORDANCE WITH MIL-STD-681. OTHER CODES AND SUFFIXES MAY BE ADDED TO THE PART NUMBER, AS NECESSARY, TO CAPTURE ANY ADDITIONAL REQUIREMENTS IMPOSED BY THE PURCHASE ORDER.

DIMENSIONS ARE IN INCHES AND, UNLESS OTHERWISE DESIGNATED, ARE NOMINAL

THIS SPECIFICATION SHEET TAKES PRECEDENCE OVER DOCUMENTS REFERENCED HEREIN. REFERENCED DOCUMENTS SHALL BE OF THE ISSUE IN EFFECT ON DATE OF INVITATION FOR BID.



Raychem Wire & Cable 501 Oakside Avenue Redwood City, CA 94063-3800 Phone: 1-800-227-8816 Fax: 1-650-361-6297

Page 1 of 1

TITLE